



ALMA MATER STUDIORUM
UNIVERSITÀ DI BOLOGNA

ARCHIVIO ISTITUZIONALE
DELLA RICERCA

Alma Mater Studiorum Università di Bologna Archivio istituzionale della ricerca

Fresh and hardened properties of cement mortars using marble sludge fines and cement sludge fines

This is the final peer-reviewed author's accepted manuscript (postprint) of the following publication:

Published Version:

Xi Y., Anastasiou E., Karozou A., Silvestri S. (2019). Fresh and hardened properties of cement mortars using marble sludge fines and cement sludge fines. *CONSTRUCTION AND BUILDING MATERIALS*, 220, 142-148 [10.1016/j.conbuildmat.2019.05.153].

Availability:

This version is available at: <https://hdl.handle.net/11585/691284> since: 2020-02-26

Published:

DOI: <http://doi.org/10.1016/j.conbuildmat.2019.05.153>

Terms of use:

Some rights reserved. The terms and conditions for the reuse of this version of the manuscript are specified in the publishing policy. For all terms of use and more information see the publisher's website.

This item was downloaded from IRIS Università di Bologna (<https://cris.unibo.it/>).
When citing, please refer to the published version.

(Article begins on next page)

This is the final peer-reviewed accepted manuscript of:

Xi Y., S. Silvestri, E. Anastasiou, and A. Karozou. 2019. "Fresh and Hardened Properties of Cement Mortars Using Marble Sludge Fines and Cement Sludge Fines." *Construction and Building Materials* 220: 142–48.

The final published version is available online at:

<http://dx.doi.org/10.1016/j.conbuildmat.2019.05.153>

Rights / License:

The terms and conditions for the reuse of this version of the manuscript are specified in the publishing policy. For all terms of use and more information see the publisher's website.

This item was downloaded from IRIS Università di Bologna (<https://cris.unibo.it/>)

When citing, please refer to the published version.

Fresh and hardened properties of cement mortars using marble sludge fines and cement sludge fines

Yuting Xi¹, Eleftherios Anastasiou², Aspasia Karouzou², Stefano Silvestri¹

¹Department of Civil Engineering, University of Bologna, Italy

²Laboratory of Building Materials, Department of Civil Engineering, Aristotle University of Thessaloniki, Greece

*Corresponding author: e-mail: elan@civil.auth.gr

Abstract

The construction sector could provide solutions for the safe utilization of industrial by-products as construction materials, if proper characterization and control of the materials properties is undertaken. Under this consideration, fines produced from marble cutting and fines produced from concrete truck washing were investigated as fine material for use in cement mortars. Both these by-products are produced in large amounts in the form of sludge. Marble Sludge Fines (MSF) and Cement Sludge Fines (CSF) were characterized in terms of fineness, density, chemical analysis and suitability for use with cement. Mortars with variable rate (10%, 20% and 30%) of cement substitution with MSF or CSF were tested and compared to a reference cement mortar in respect to their fresh and hardened properties. Packing ability and viscosity were measured in fresh mortars, while strength development, water absorption and porosity were measured in hardened mortars. The results confirm the suitability of both as filler material; although MSF performed better regarding fresh mortar properties and CSF showed better results regarding strength development.

Keywords: cement mortars; marble sludge fines; cement sludge fines; industrial by-products.

1. Introduction

By-products from industrial processes are being produced in large amounts around the world and their handling, processing and disposal is taking up considerable effort and increasing financial and environmental cost [1,2]. It is estimated that the amount of waste generated during cutting, sawing and shaping of ornamental marble accounts for 20-25% of the total marble processed [3], resulting in huge amounts of marble waste. Marble waste is either produced as large pieces that are left over in primary cutting, which find various uses as aggregates [4,5]; or as fine material produced in wet condition from sawing and shaping, named marble powder, marble dust or marble sludge fines (MSF), which is being investigated as filler for construction applications [6–8]. Concrete production, on the other hand, is also generating large amounts of waste; depending on local practices, it is estimated that 1~9% of fresh concrete is returned to the concrete batching plant [9]. This accounts for huge amounts of waste as the annual global consumption of concrete exceeds 10 billion tons [10]. The returned fresh concrete has several possible uses, including immediate recycling or use as a source for recycled concrete aggregates [11–13], however, the material adhered to the inside of the barrel is washed and stored in sedimentation tanks, as it has high alkalinity [14]. The alkaline water from the sedimentation tanks finds some use replacing fresh water in concrete production [15–17] and the remaining material, named cement waste slurry or cement sludge fines (CSF) finds little or no use.

Both MSF and CSF consist of fine particles and are produced in wet condition, which makes handling and processing more difficult, since some processing is usually required prior to transportation or use [18].

43 Their use as fine material, however, could provide an alternative for the construction industry, which consumes
44 considerable amounts of filler material from natural sources [19]. Relevant literature from Corinaldesi et al.
45 [20] reported that marble powder showed the filler effect that improves early age strength in mortars and
46 recommended 10% as optimum cement substitution rate. Hameed et al. [21] found that marble sludge fines
47 used as filler in self-compacting concrete decreased viscosity and improved segregation resistance, suggesting
48 a limited use of 15% by total powder weight. Omar et al. [22] used marble powder as sand replacement in
49 concrete and verified its filler effect, while they also reported a strength increase at 15% sand replacement rate.
50 Aliabdo et al. [23] tested marble dust as cement or as sand replacement at various rates up to 15% wt. and
51 confirmed its compatibility for use with cement, while they reported a decrease in cement mortar and concrete
52 strength when MSF was used as cement replacement and an increase in concrete strength when MSF was used
53 as sand replacement. Ulubeyli et al. [24] used the waste marble in the conventional concrete as binder or
54 fine/coarse aggregate and it positively affected properties of hardened concrete, whereas in self-compacting
55 concrete, the increase of waste marble replacement ratios decreased its mechanical properties. Sardinha et al.
56 [25] studied the durability of concrete with MSF as cement replacement and reported that it generally decreased
57 with increased MSF use, while at low replacement levels (5%) the durability reduction could be offset with
58 the use of superplasticizers. It must be noted though, that the authors used a rather coarse MSF, with only 27.5%
59 passing through the 125 μm sieve. Mashaly et al. [26] used MSF sized below 100 μm as cement replacement
60 in concrete and reported an increase in water demand and also an increase in mechanical strength at
61 replacement rates up to 20%.

62 The research on CSF properties and utilization is clearly more limited: Zervaki et al. [27] found an
63 improvement in compressive strength of mortars when untreated CSF was used, without any removal of its
64 free water content. However, when it exceeded a certain concentration, it led to loss of workability. Moreover,
65 dry de-agglomerated CSF, when used in mortars as a cement replacement at 2% ratio, caused a slight
66 improvement in compressive strength, due to the filler effect. In higher replacement ratios a slight decrease of
67 compressive strength was detected. Audo et al. [28] tested the incorporation of CSF plants as limestone fillers
68 in mortars and reported a decrease in the workability of the fresh mortar and a variability in the compressive
69 strength of the hardened mortars, between -30% and +17%, compared to the reference. Hossain et al. [29]
70 reported that the concrete slurry waste generated from ready-mixed concrete plants is classified as a corrosive
71 hazardous material and used the accelerated carbonation technique in order to produced hardened products.
72 Correia et al. [30] replaced natural fine aggregates with the fresh concrete waste (FCW). The recycled new
73 concretes were in various water/cement ratios and the results showed that the fresh concrete workability
74 worsened with the increase in FCW content but the water absorption (5–10 wt.%), 7-day compressive strength
75 (26–36 MPa) and 28-day compressive strength (32–44 MPa) remained within the specified ranges.

76 Following existing literature, the present study attempts to properly introduce MSF and CSF in cement-
77 based mortars as supplementary cementitious materials. The fineness of the two by-products shows that their
78 optimal use would be as cement-replacement fillers, provided that they are suitable for such a use. Hence,
79 material characterization is carried out firstly, followed by testing cement mortars with cement replacement
80 rates of up to 30%. The suitability for use as filler is investigated by a series of physical and analytical tests,
81 including fineness determination and chemical analysis. Regarding mortars, 10%, 20%, and 30% wt. cement
82 replacement rates were chosen for both materials, as these rates are sufficient to describe the effect of filler use
83 with cement. Since the fresh mortar properties were expected to be affected, workability, viscosity and packing
84 ability were determined, while the hardened properties investigated were compressive and flexural strength at
85 various ages, water absorption and porosity. The two by-products show some similarities and the research aims
86 also at comparing their effectiveness as fillers for cement mortar production, while pointing out any potential

87 advantages or disadvantages from their use.

88

89 2. Materials and methods

90 2.1 Materials characterization

91 In this study, Portland cement CEM I 42.5 N, produced according to EN-197-1 was used as reference.
92 The industrial by-products (MSF and CSF) were received in wet condition, both containing about 40% water.
93 Although the two by-products could be used as received and, therefore, avoid the cost and energy for drying,
94 it was decided at first to use them in dry condition for two reasons; Firstly, because transportation of
95 construction materials in wet condition is usually more costly and, secondly, because the granulometry of the
96 dried material can be controlled more easily by crushing and sieving. In order to achieve uniformity for testing,
97 MSF and CSF were air-dried at 40°C until constant mass and then they were crushed and sieved in order to
98 obtain fines of grain size less than 0.075 mm. The particle size distribution of all the materials used was then
99 measured using a Malvern Mastersizer 2000 laser particle size analyzer.

100

101 In order to determine the suitability of MSF and CSF for use with cement, a series of characterization
102 tests was carried out. The chemical composition of MSF, CSF and of the reference CEM I 42.5 N cement used
103 were determined using Atomic Absorption Spectroscopy (AAS), as total oxides of metals by digestion using a
104 mixture of concentrated acids, AAnalyst 400, Perkin Elmer. Loss on ignition (L.I. %) was determined at
105 1000 °C. Additionally, their water-soluble salts were determined using Ionic Chromatography, as anions of
106 salts extracted with distilled water and then filtered, Dionex, while simultaneous Differential Thermal –
107 Thermogravimetric Analysis (DTA-TG), SDT 2960 TA Instruments, was used for the determination of the
108 calcium carbonate (CaCO₃) content of MSF and CSF, under a N₂ atmosphere from 10 °C to 1000 °C. The
109 apparent specific density of the fines used was determined using a Le Chatelier flask according to ASTM
110 C188-14 [31], while their mineralogical composition was determined using a PW 1840 Philips diffractometer
111 (XRD). Since the test materials were tested as cement replacement materials, it was decided to measure their
112 effect on setting time and expansion of ordinary cement according to EN 196-3 [32]. For this reason, seven
113 cement pastes of standard consistence were prepared; one using 100% CEM I 42.5 N; three 10%, 20% and 30%
114 MSF w/w as cement replacement; and three using 10%, 20% and 30% CSF w/w as cement replacement. As
115 the replacement of cement with alternative binders may alter water retentivity and workability, the water
116 required for standard consistence was recorded.

117

118 2.2 Design of experimental testing on mortars

119 Test mortars were prepared in the laboratory, by using 1 part binder; 3 parts sand; and 0.5 parts water. All
120 mortar mixtures were prepared with CEM I 42.5 N cement and natural siliceous river sand conforming to
121 ASTM C33/C33M-13 [33]. MSF and CSF were used as cement replacement at rates of 10%, 20%, and 30%,
122 resulting in seven different mortars, according to Table 1.

123

124 Table 1. Constituents of test mortars.

Constituents [g]	R (Reference)	M10	M20	M30	C10	C20	C30
CEM I 42.5	450	405	360	315	405	360	315
MSF	0	45	90	135	0	0	0
CSF	0	0	0	0	45	90	135

Water	225	225	225	225	225	225	225
Sand	1350	1350	1350	1350	1350	1350	1350
Superplasticizer (% of total binder)	0.5	0.5	0.6	0.6	0.8	1.0	1.2

125

126 The water to binder ratio was selected to be constant at 0.50, in order to properly assess the effect of
127 cement replacement on strength. Therefore, a polycarboxylate-based superplasticizer was used in varying rates,
128 in order to achieve similar consistence for all fresh mixtures. The required consistence was 150 ± 10 mm
129 diameter at the flow table test, according to EN 1015-3 [34]. The amount of superplasticizer required in order
130 to achieve the required consistence served also as an indication of water retentivity of MSF and CSF, as well
131 as a measure of their effect on workability. An ICAR rheometer was used in order to determine the plastic
132 viscosity of the fresh mortars using the Bingham model [35,36].

133 Since MSF and CSF have similar or finer particle size distribution than cement, their effect on packing
134 of the wet mortar was investigated. The wet packing method proposed by Wong and Kwan [37] was followed,
135 by measuring the weight of the compacted fresh mortar in a reference mould and then by calculating the solid
136 concentration ϕ of the granular material according to equations (1) and (2).

137
$$V_c = \frac{M}{\rho_w \cdot u_w + \rho_c \cdot R_c + \rho_{msf} \cdot R_{msf} + \rho_{csf} \cdot R_{csf} + \rho_s \cdot R_s} \quad (1)$$

138
$$\phi = \frac{V_c}{V} \quad (2)$$

139 in which V_c is the solid volume of the solid materials used, M and V are the mass and volume, respectively, of
140 the wet mortar in the reference mould $\rho_w, \rho_c, \rho_{msf}, \rho_{csf}, \rho_s$ are the densities of water, cement, MSF, CSF and sand,
141 respectively, u_w is the water ratio, equal to the water to cementitious ratio by volume, and R_c, R_{msf}, R_{csf} and R_s
142 are the volumetric ratios of cement, MSF, CSF and sand, respectively.

143 After mixing, the 40 x 40 x 160 mm specimens were cast, compacted and cured in an environmental
144 chamber, at $20^\circ\text{C} \pm 2^\circ\text{C}$ and $95\% \pm 5\%$ relative humidity until testing. Compressive strength was measured at
145 3, 7 and 28 days, while flexural strength, porosity, capillary absorption and apparent specific density were
146 measured at 28 days. The porosity measurement was conducted according to RILEM CPC 11.3 [38], in which
147 the specimens were submerged in the water under vacuum and capillary tests were performed according to EN
148 1015-18 [39].


149

150 3. Results and discussion

151 3.1 MSF and CSF properties

152 The particle size distribution of cement, MSF, CSF and natural sand can be seen in Figure 1. The natural
153 sand used showed a gradation of 50 to 4000 μm , while the three binders were considerably finer; MSF shows
154 grain sizes of 0.5 to 80 μm , CSF was sized 0.5 to 400 μm , while cement ranges from 3 to 80 μm . Overall, MSF
155 seems to be finer than cement, while CSF is of similar average fineness, but has a broader range of grain sizes.
156 When MSF and CSF are used for cement substitution in mortars, the difference in particle size distribution is
157 expected to have an effect on the workability and packing ability of the produced mortars.

158



159

160 Figure 1. Particle size distribution of the materials used.

161

162 The apparent specific density CEM I 42.5 N, MSF and CSF was measured 3140 kg/m³, 2443 kg/m³ and
 163 2556 kg/m³, respectively, according to ASTM C188-14 [31], while the apparent specific density of the natural
 164 sand was measured 2636 kg/m³, according to ASTM C128-15 [40]. The chemical analysis of CEM I 42.5 N,
 165 MSF and CSF are shown in Table 2. MSF consists mostly of calcium in the form of calcite (Figure 2), which is
 166 expected, because it originates from limestone marble sawing. Its chemical composition is similar to that of
 167 limestone filler [41] and the high loss of ignition accounts for its carbonate content, which reaches 98.3% wt. (Figure
 168 4).

169

170 Table 2. Chemical composition of binders (% w.t.)


Constituents	Na ₂ O	K ₂ O	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	SiO ₂	L.I.%	Cl ⁻	NO ₃ ⁻	SO ₃
CEM I 42.5 N	0.57	1.08	66.80	3.91	2.40	3.74	19.60	1.91	0.03	0.02	1.49
MSF	0.21	0.09	53.02	1.59	0.28	1.14	1.68	41.99	0.03	0.01	0.41
CSF	0.15	0.24	55.07	1.63	1.74	2.80	1.48	36.09	0.03	<0.01	0.34

171


172 CSF showed a very similar chemical composition to that of MSF and the siliceous content originating from
 173 cement hydrates was probably excluded in the sieving process. Crushing and sieving of CSF and MSF was
 174 used to release more fine material from brittle agglomerates, rather than reduce the whole fraction
 175 below 75 μm, which would be more costly. As a result, the harder compounds in CSF were not crushed
 176 and were also probably retained in the 75 μm. Both alternative fine materials had low salts contents and are
 177 suitable for cement substitution in this respect. CSF originally consists mostly of hardened cement paste and fine
 178 limestone aggregates; therefore, its CaO and SiO₂ contents were not expected to be reactive. The XRD diagram
 179 (Figure 3) shows that the mineralogical composition of CSF was mainly calcite. Also, an absence of C₃S and
 180 traces of C₂S peaks were observed. The latter may indicate full hydration of the sludge. Also, a strength
 181 development test with lime according to ASTM C593-95 [42] showed minimal strength development at 28
 182 days (<0.50 MPa), which implies that there is no significant pozzolanic activity from CSF. The high value of
 183 loss on ignition (L.I. %) can be attributed to the bonded water proportion and CO₂ quantity that was emitted from

184 the sample. Indeed, according to the DTA-TG analysis (Figure 5), the loss of volatile compounds (green line of the
185 diagram) accounted 29.8% for the loss of carbon dioxide, CO₂, and 0.4741% (or 0.18 w.t.%) for the dihydroxylation
186 of portlandite, Ca(OH)₂. The presence of a high amount of CaCO₃ (67.77 wt%) was also verified.

187 The results of the analytical tests imply that both MSF and CSF are fine materials without any hydraulic
188 or pozzolanic properties. The fact that they can be easily crushed and sieved through the 75 μm implies a
189 probable use as filler materials. Regarding handling and processing, it would be preferable to use MSF and
190 CSF in their original wet condition in order to avoid the drying process; however, further research is required
191 in this direction.




192
193 Figure 2. XRD diagram of MSF, where C: calcite.




194
195 Figure 3. XRD diagram of CSF, where C: calcite.

196
197
198



199
 200
 201
 202
 203
 204

Figure 4. Differential thermal–thermogravimetric analysis (DTA-TGA) analysis of MSF and quantification of calcite content as a percentage by mass of sample.



205
 206
 207
 208
 209

Figure 5. Differential thermal–thermogravimetric analysis (DTA-TGA) analysis of CSF and quantification of calcite content as a percentage by mass of sample.

210 From the results of Table 3, it seems that cement substitution with MSF does not alter water
 211 requirement significantly, while the initial setting time increased slightly at 10% substitution, but the
 212 effect diminished at higher replacement rates. Despite an increased value for 20% replacement, which is
 213 way below the threshold value of 10 mm according to EN 196-3, MSF use also does not produce
 214 considerable expansion in the cement pastes. CSF use on the other hand, seems to increase the water

215 requirement for standard consistence, which explains the increased superplasticizer used in the mortars
 216 with CSF in Table 1, in order to have the same workability of fresh mortars. The initial setting time
 217 increased slightly with increased CSF use, but still way below the maximum allowed increase value of
 218 120 min according to EN 206-1 [43], while Le Chatelier soundness remained unchanged with increased
 219 CSF use. The variations in initial setting time can be explained by the different coarseness and surface
 220 hardness of the grains of MSF and CSF, in respect to the filler effect.
 221

222 Table 3. Effect of cement replacement with MSF or CSF on setting time and soundness of pastes.

Constituents [% of binder]	Reference	MSF10	MSF20	MSF30	CSF10	CSF20	CSF30
CEM I 42.5	100%	90%	80%	70%	90%	80%	70%
MSF	0	10%	20%	30%	0	0	0
CSF	0	0	0	0	10%	20%	30%
Water/binder for standard consistence	0.296	0.298	0.300	0.296	0.314	0.360	0.376
Initial setting time [min]	187	207	191	182	199	203	204
Le Chatelier soundness [mm]	1.2	0.9	2.7	0.4	1.0	0.5	1.1

223

224 3.2 Results from testing mortars

225 3.2.1 Fresh mortar properties

226 As it can be seen from Table 1 and already commented in the previous paragraph, CSF use required an
 227 increased amount of superplasticizer in order for the mortar to reach the required workability. Regarding plastic
 228 viscosity resulting from the Bingham model and packing ability as expressed by solid concentration ϕ , of the
 229 fresh mortars, the results are presented in Table 4.
 230

231 Table 4. Viscosity and packing ability measurements in fresh test mortars.

Test mortars	reference	M10	M20	M30	C10	C20	C30
Plactic viscosity (Pa.s)	7.9	-	6.7	14.2	3.9	15.7	27.7
Solid concentration ϕ	0.694	0.718	0.726	0.732	0.694	0.703	0.700


232

233 The results show that a high replacement rate of cement would render the fresh mortar more viscous,
 234 compared to the reference. Although M10 did not yield reliable result, at lower replacement rates (up to 20%
 235 for MSF and 10% for CSF) viscosity seems to decrease compared to the reference. A certain level of viscosity
 236 is required for the mortars to be easily compacted, but in other cases, a higher viscosity serves as resistance to
 237 segregation in highly flowable mortars. Although both test materials alter viscosity, MSF seems to produce
 238 mortars of lower viscosity compared to CSF. This can be attributed to the increased fineness of MSF compared
 239 to CSF. Indeed, the fineness of MSF contributes also to a higher packing, as expressed by the increase in solid
 240 concentration compared to the reference mortar, which increases proportionally to the rate of MSF use. CSF
 241 on the other hand, does not alter solid concentration significantly, owing to the similar particle size distribution
 242 to cement, as shown already in Figure 1.
 243

244


244 3.2.2 Hardened mortar properties

245 Regarding mortar strength development, increasing MSF use results in reducing compressive strength
 246 (Figure 6), however at 10% cement replacement rate, mortars with MSF exhibit 98.0% and 91.7% of the
 247 reference compressive strength at 7 and 28 days, respectively. The early age strength development of mortars
 248 with MSF may be attributed to the filler effect.
 249



250
 251 Figure 6. Compressive strength development of cement mortars with MSF.
 252

253 When CSF was used as 10% cement replacement, no reduction in strength development was observed
 254 (Figure 7). By increasing the rate of cement replacement, compressive strength decreased, but at 20% CSF use
 255 the mortars reached 93.8% and 94.5% of the reference compressive strength at 7 and 28 days, respectively.
 256 Although the filler effect also explains early strength development, CSF seems to perform better compared to
 257 MSF regarding cement hydration. This occurrence could be attributed to the considerably higher alkalinity of
 258 CSF (pH = 12.1), compared to MSF (pH = 9.7), which facilitates cement hydration. When a filler is added in
 259 a certain percentage, it influences the pH value of the binders in the pore solution. If the pH is reduced, this
 260 affects the hydration and as a result the compressive strength [44].
 261




262

263 Figure 7. Compressive strength development of cement mortars with CSF.

264

265 Flexural strength on the other hand, reduced in all cases, and the reduction was proportional to cement
 266 replacement (Figure 8). The flexural strength ranged from 88.3% of the reference for 10% MSF use to 67.6%
 267 of the reference for 30% CSF use. This indicates that the interfacial transition zone between the cement matrix
 268 and the aggregate, deteriorated when the industrial by-products were used and the deterioration can be
 269 attributed to the surface characteristics and water absorption of the MSF and CSF particles. Indeed, CSF, which
 270 showed increased water retentivity at the mortar production stage, showed higher decrease in flexural strength
 271 development.



272

273 Figure 8. 28-day flexural strength of cement mortars with MSF or CSF.

274

275 The capillary absorption and porosity results shown in Table 5 validate the above statement, since mortars
 276 with CSF show increased absorption, porosity and capillary coefficient, compared to mortars with MSF. The
 277 reference mortar shows the lowest values in these three tests, while increasing cement replacement increases
 278 absorption and porosity values proportionally. In addition, the apparent specific density of the mortars reduced
 279 with increased cement replacement, as expected, but CSF use reduced density more than MSF, despite having
 280 itself higher density compared to MSF. This also implies that CSF use resulted in more voids in the cement
 281 matrix and can be attributed to the coarser granulometry and higher water retentivity of CSF compared to MSF.

282

283 Table 5. Physical properties of mortars with MSF and CSF.

Constituents	Reference	M10	M20	M30	C10	C20	C30
Apparent specific density [kg/m ³]	2152	2068	2074	2065	2056	2062	2030
Absorption [%]	1.6	2.8	2.7	3.8	3.2	5.0	4.4
Porosity [%]	3.5	5.9	5.5	7.8	6.6	10.3	9.0
Capillary coefficient c [g/cm ² *min ^{1/2}]	0.043	0.057	0.066	0.103	0.088	0.112	0.122

284

285 4. Conclusions

286 The results show that the two by-products (MSF and CSF) share considerable similarities; they have

287 similar chemical composition, consisting mostly of calcium carbonate; they are both largely inert; and their
288 fineness renders their most probable use as fillers. In addition, they are both produced in wet condition and
289 require similar processing and handling prior to use (drying, crushing, sieving). MSF and CSF, when
290 investigated as supplementary cementitious materials by replacing cement in mortars, also showed some
291 differences that must be taken into account. MSF was finer, had lower water retention than CSF, and therefore
292 provided better packing ability, resulting in lower absorption and porosity of the hardened mortar; CSF on the
293 other hand showed higher compressive strength values compared to MSF, when used as 10%, 20% or 30% wt.
294 cement replacement, probably owing to its higher alkalinity.

295 Based on the results, it seems that both MSF and CSF can be used as filler for cement replacement in
296 mortars, since their intrinsic properties, including fineness, chemical composition and reactivity seem adequate
297 for such a use, while the strength reduction obtained is reasonable. Further research is required, of course,
298 regarding utilization in wet condition and quality control of the materials.

300 **Funding**

301 This research did not receive any specific grant from funding agencies in the public, commercial, or not-for-
302 profit sectors.

304 **Acknowledgements**

305 Author Karozou A. would like to thank the General Secretariat for Research and Technology (GSRT) and the
306 Hellenic Foundation for Research and Innovation (HFRI) for funding the research through the scholarship
307 foundation program for PhD candidates.

309 **References**

- 310 [1] R.L. Paquin, T. Busch, S.G. Tilleman, Creating Economic and Environmental Value through Industrial
311 Symbiosis, *Long Range Planning*. 48 (2015) 95–107. doi:10.1016/J.LRP.2013.11.002.
- 312 [2] L.D. Poulikakos, C. Papadaskalopoulou, B. Hofko, F. Gschösser, A. Cannone Falchetto, M. Bueno, M.
313 Arraigada, J. Sousa, R. Ruiz, C. Petit, M. Loizidou, M.N. Partl, Harvesting the unexplored potential of
314 European waste materials for road construction, *Resources, Conservation and Recycling*. 116 (2017)
315 32–44. doi:10.1016/J.RESCONREC.2016.09.008.
- 316 [3] F. Saboya, G.C. Xavier, J. Alexandre, The use of the powder marble by-product to enhance the
317 properties of brick ceramic, *Construction and Building Materials*. 21 (2007) 1950–1960.
318 doi:10.1016/J.CONBUILDMAT.2006.05.029.
- 319 [4] H. Şahan Arel, Recyclability of waste marble in concrete production, *Journal of Cleaner Production*.
320 131 (2016) 179–188. doi:10.1016/J.JCLEPRO.2016.05.052.
- 321 [5] S.D. Kore, A.K. Vyas, Impact of marble waste as coarse aggregate on properties of lean cement concrete,
322 *Case Studies in Construction Materials*. 4 (2016) 85–92. doi:10.1016/J.CSCM.2016.01.002.
- 323 [6] B. Demirel, K.E. Alyamaç, Waste marble powder/dust, Waste and Supplementary Cementitious
324 Materials in Concrete. (2018) 181–197. doi:10.1016/B978-0-08-102156-9.00006-7.
- 325 [7] M. Galetakis, A. Soutana, A review on the utilisation of quarry and ornamental stone industry fine by-
326 products in the construction sector, *Construction and Building Materials*. 102 (2016) 769–781.
327 doi:10.1016/J.CONBUILDMAT.2015.10.204.
- 328 [8] R. Rodrigues, J. de Brito, M. Sardinha, Mechanical properties of structural concrete containing very
329 fine aggregates from marble cutting sludge, *Construction and Building Materials*. 77 (2015) 349–356.
330 doi:10.1016/J.CONBUILDMAT.2014.12.104.

- 331 [9] D. Xuan, B. Zhan, C.S. Poon, W. Zheng, Innovative reuse of concrete slurry waste from ready-mixed
 332 concrete plants in construction products, *Journal of Hazardous Materials*. 312 (2016) 65–72.
 333 doi:10.1016/j.jhazmat.2016.03.036.
- 334 [10] S.A. Miller, A. Horvath, P.J.M. Monteiro, Readily implementable techniques can cut annual CO₂
 335 emissions from the production of concrete by over 20%, *Environmental Research Letters*. 11 (2016)
 336 074029. doi:10.1088/1748-9326/11/7/074029.
- 337 [11] S. Kou, B. Zhan, C. Poon, Feasibility study of using recycled fresh concrete waste as coarse aggregates
 338 in concrete, *Construction and Building Materials*. 28 (2012) 549–556.
 339 doi:10.1016/J.CONBUILDMAT.2011.08.027.
- 340 [12] A. Kazaz, S. Ulubeyli, Current Methods for the Utilization of the Fresh Concrete Waste Returned to
 341 Batching Plants, *Procedia Engineering*. 161 (2016) 42–46. doi:10.1016/J.PROENG.2016.08.495.
- 342 [13] N.N. Gebremichael, S.M. Motahari Karein, M. Karakouzian, K. Jadidi, Investigation of setting time
 343 and compressive strength of ready-mixed concrete blended with returned fresh concrete, *Construction
 344 and Building Materials*. 197 (2019) 428–435. doi:10.1016/J.CONBUILDMAT.2018.11.201.
- 345 [14] L. de B.P. Vieira, A.D. de Figueiredo, Evaluation of concrete recycling system efficiency for ready-mix
 346 concrete plants, *Waste Management*. 56 (2016) 337–351. doi:10.1016/j.wasman.2016.07.015.
- 347 [15] S. Tsimas, M. Zervaki, Reuse of waste water from ready-mixed concrete plants, *Management of
 348 Environmental Quality: An International Journal*. 22 (2011) 7–17. doi:10.1108/14777831111098444.
- 349 [16] B. Chatveera, P. Lertwattanaruk, N. Makul, Effect of sludge water from ready-mixed concrete plant on
 350 properties and durability of concrete, *Cement and Concrete Composites*. 28 (2006) 441–450.
 351 doi:10.1016/J.CEMCONCOMP.2006.01.001.
- 352 [17] G. Asadollahfardi, M. Asadi, H. Jafari, A. Moradi, R. Asadollahfardi, Experimental and statistical
 353 studies of using wash water from ready-mix concrete trucks and a batching plant in the production of
 354 fresh concrete, *Construction and Building Materials*. 98 (2015) 305–314.
 355 doi:10.1016/j.conbuildmat.2015.08.053.
- 356 [18] D. Xuan, C.S. Poon, W. Zheng, Management and sustainable utilization of processing wastes from
 357 ready-mixed concrete plants in construction: A review, *Resources, Conservation and Recycling*. 136
 358 (2018) 238–247. doi:10.1016/J.RESCONREC.2018.04.007.
- 359 [19] U.S. Geological Survey, Mineral commodity summaries 2018, 2018.
 360 doi:https://doi.org/10.3133/70194932.
- 361 [20] V. Corinaldesi, G. Moriconi, T.R. Naik, Characterization of marble powder for its use in mortar and
 362 concrete, *Construction and Building Materials*. 24 (2010) 113–117.
 363 doi:10.1016/J.CONBUILDMAT.2009.08.013.
- 364 [21] M.S. Hameed, A.S.S. Sekar, L. Balamurugan, V. Saraswathy, Self-compacting concrete using Marble
 365 Sludge Powder and Crushed Rock Dust, *KSCE Journal of Civil Engineering*. 16 (2012) 980–988.
 366 doi:10.1007/s12205-012-1171-y.
- 367 [22] O.M. Omar, G.D. Abd Elhameed, M.A. Sherif, H.A. Mohamadien, Influence of limestone waste as
 368 partial replacement material for sand and marble powder in concrete properties, *HBRC Journal*. 8 (2012)
 369 193–203. doi:10.1016/j.hbrcj.2012.10.005.
- 370 [23] A.A. Aliabdo, A.E.M. Abd Elmoaty, E.M. Auda, Re-use of waste marble dust in the production of
 371 cement and concrete, *Construction and Building Materials*. 50 (2014) 28–41.
 372 doi:10.1016/j.conbuildmat.2013.09.005.
- 373 [24] G.C. Ulubeyli, R. Artir, Properties of Hardened Concrete Produced by Waste Marble Powder, *Procedia
 374 - Social and Behavioral Sciences*. 195 (2015) 2181–2190. doi:10.1016/j.sbspro.2015.06.294.

- 375 [25] M. Sardinha, J. de Brito, R. Rodrigues, Durability properties of structural concrete containing very fine
376 aggregates of marble sludge, *Construction and Building Materials*. 119 (2016) 45–52.
377 doi:10.1016/J.CONBUILDMAT.2016.05.071.
- 378 [26] A.O. Mashaly, B.A. El-Kaliouby, B.N. Shalaby, A.M. El – Gohary, M.A. Rashwan, Effects of marble
379 sludge incorporation on the properties of cement composites and concrete paving blocks, *Journal of*
380 *Cleaner Production*. 112 (2016) 731–741. doi:10.1016/J.JCLEPRO.2015.07.023.
- 381 [27] M. Zervaki, C. Leptokaridis, S. Tsimas, Reuse of By-Products from Ready-Mixed Concrete Plants for
382 the Production of Cement Mortars, *Journal of Sustainable Development of Energy, Water and*
383 *Environment System*. 1 (2013) 152–162. doi:10.13044/j.sdewes.2013.01.0011.
- 384 [28] M. Audo, P.Y. Mahieux, P. Turcry, Utilization of sludge from ready-mixed concrete plants as a substitute
385 for limestone fillers, *Construction and Building Materials*. 112 (2016) 790–799.
386 doi:10.1016/j.conbuildmat.2016.02.044.
- 387 [29] M.U. Hossain, D. Xuan, C.S. Poon, Sustainable management and utilisation of concrete slurry waste:
388 A case study in Hong Kong, *Waste Management*. 61 (2017) 397–404.
389 doi:10.1016/J.WASMAN.2017.01.038.
- 390 [30] S.L. Correia, F.L. Souza, G. Dienstmann, A.M. Segadães, Assessment of the recycling potential of fresh
391 concrete waste using a factorial design of experiments, *Waste Management*. 29 (2009) 2886–2891.
392 doi:10.1016/J.WASMAN.2009.06.014.
- 393 [31] ASTM C188-14, Standard Test Method for Density of Hydraulic Cement, 2014.
- 394 [32] EN 196-3, Methods of testing cement. Determination of setting times and soundness, 2005.
- 395 [33] ASTM C33 / C33M-13, Standard Specification for Concrete Aggregates, 2013.
- 396 [34] EN 1015-3, Methods of test for mortar for masonry - Determination of consistence of fresh mortar (by
397 flow table), 1999.
- 398 [35] J.E. Wallevik, Relationship between the Bingham parameters and slump, *Cement and Concrete*
399 *Research*. 36 (2006) 1214–1221. doi:10.1016/J.CEMCONRES.2006.03.001.
- 400 [36] D. Feys, K.H. Khayat, Comparing Rheological Properties of SCC Obtained with the ConTec and ICAR
401 Rheometers, Fifth North American Conference on the Design and Use of Self-Consolidating Concrete,
402 12-15 May. (2013) 1–11.
- 403 [37] H.H.C. Wong, A.K.H. Kwan, Packing density of cementitious materials: part 1—measurement using a
404 wet packing method, *Materials and Structures*. 41 (2008) 689–701. doi:10.1617/s11527-007-9274-5.
- 405 [38] CPC 11.3. Absorption d’eau par immersion sous vide, *Matériaux et Constructions*. 17 (1984) 391–394.
406 doi:10.1007/BF02478713.
- 407 [39] EN 1015-18, Determination of water absorption coefficient due to capillary action of hardened mortar,
408 2002.
- 409 [40] ASTM C128-15, Standard Test Method for Relative Density (Specific Gravity) and Absorption of Fine
410 Aggregate, 2015.
- 411 [41] S. Tsivilis, G. Batis, E. Chaniotakis, G. Grigoriadis, D. Theodossis, Properties and behavior of
412 limestone cement concrete and mortar, *Cement and Concrete Research*. 30 (2000) 1679–1683.
413 doi:10.1016/S0008-8846(00)00372-0.
- 414 [42] ASTM C593-95(2000), Standard Specification for Fly Ash and Other Pozzolans for Use With Lime,
415 2000.
- 416 [43] EN 206-1, Concrete. Part 1: Specification, performance, production and conformity, 2005.
- 417 [44] K. De Weerd, M. Ben Haha, G. Le Saout, K.O. Kjellsen, H. Justnes, B. Lothenbach, Hydration
418 mechanisms of ternary Portland cements containing limestone powder and fly ash, *Cement and*

419 Concrete Research. 41 (2011) 279–291. doi:10.1016/J.CEMCONRES.2010.11.014.
420