

Alma Mater Studiorum Università di Bologna Archivio istituzionale della ricerca

Exploiting fast exciton diffusion in dye-doped polymer nanoparticles to engineer efficient photoswitching

This is the final peer-reviewed author's accepted manuscript (postprint) of the following publication:

Published Version:

Exploiting fast exciton diffusion in dye-doped polymer nanoparticles to engineer efficient photoswitching / Trofymchuk, Kateryna; Prodi, Luca; Reisch, Andreas; Mély, Yves; Altenhöner, Kai; Mattay, Jochen; Klymchenko, Andrey S.. - In: THE JOURNAL OF PHYSICAL CHEMISTRY LETTERS. - ISSN 1948-7185. -STAMPA. - 6:12(2015), pp. 2259-2264. [10.1021/acs.jpclett.5b00769]

Availability:

This version is available at: https://hdl.handle.net/11585/520987 since: 2017-01-30

Published:

DOI: http://doi.org/10.1021/acs.jpclett.5b00769

Terms of use:

Some rights reserved. The terms and conditions for the reuse of this version of the manuscript are specified in the publishing policy. For all terms of use and more information see the publisher's website.

This item was downloaded from IRIS Università di Bologna (https://cris.unibo.it/). When citing, please refer to the published version.

(Article begins on next page)

This is the final peer-reviewed accepted manuscript of:

Trofymchuk, Kateryna; Prodi, Luca; Reisch, Andreas; Mély, Yves; Altenhöner, Kai; Mattay, Jochen; Klymchenko, Andrey S., Exploiting fast exciton diffusion in dyedoped polymer nanoparticles to engineer efficient photoswitching, «THE JOURNAL OF PHYSICAL CHEMISTRY LETTERS», 2015, 6, pp. 2259 – 2264

Thefinalpublishedversionisavailableonlineat:http://dx.doi.org/10.1021/acs.jpclett.5b00769

Rights / License:

The terms and conditions for the reuse of this version of the manuscript are specified in the publishing policy. For all terms of use and more information see the publisher's website.

This item was downloaded from IRIS Università di Bologna (<u>https://cris.unibo.it/</u>)

When citing, please refer to the published version.

Exploiting Fast Exciton Diffusion in Dye-Doped Polymer Nanoparticles to Engineer Efficient Photoswitching

Kateryna Trofymchuk,^a Luca Prodi,^b Andreas Reisch,^a Yves Mély,^a Kai Altenhöner,^c Jochen Mattay,^c and Andrey S. Klymchenko^{a,*}

^aLaboratoire de Biophotonique et Pharmacologie, UMR 7213 CNRS, Université de Strasbourg, Faculté de Pharmacie, 74, Route du Rhin, 67401 ILLKIRCH Cedex, France.

^bDipartimento di Chimica "Giacomo Ciamician", Università degli Studi di Bologna, via Selmi 2, 40126 Bologna, Italy.

^cOrganic Chemistry I, Department of Chemistry, Bielefeld University, Universitätsstr. 25, 33615 Bielefeld, Germany.

AUTHOR INFORMATION

Corresponding Author:

*Andrey S. Klymchenko, e-mail: andrey.klymchenko@unistra.fr; Tel: +33 368 85 42 55.

ABSTRACT

Photoswitching of bright fluorescent nanoparticles opens new possibilities for bioimaging with superior temporal and spatial resolution. However, efficient photoswitching of nanoparticles is hard to achieve using Förster resonance energy transfer (FRET) to a photochromic dye, because the particle size is usually larger than the Förster radius. Here, we propose to exploit the exciton diffusion within the FRET donor dyes to boost photoswitching efficiency in dye-doped polymer nanoparticles. To this end, we utilized bulky hydrophobic counterions that prevent self-quenching and favor communication of octadecyl rhodamine B dyes inside a polymer matrix of poly(D,L-lactide-*co*-glycolide). Among tested counterions, only perfluorinated tetraphenylborate that favors the exciton diffusion enables high photoswitching efficiency (on/off ratio ~20). The switching improves with donor dye loading and requires only 0.1-0.3 wt% of a diphenylethene photochromic dye. Our nanoparticles were validated both in solution and at the single-particle level. The proposed concept paves the way to new efficient photoswitchable nanomaterials.

TOC GRAPHICS



KEYWORDS: fluorescent nanoparticles, PLGA polymer, photochromic dye, energy transfer, exciton diffusion, bulky hydrophobic counterions, single-particle microscopy

Photoswitchable fluorescence systems gain growing attention because of numerous potential applications, particularly for fluorescence imaging with superior resolution.¹⁻⁴ The fluorescence switching requires coupling of the photo-induced chemical transformation with the fluorescence output.5 This can be achieved with so-called photochromic dyes, where the light-induced chemical changes are associated with change of their optical properties.⁶ Two approaches are used in this case. The first one exploits fluorescent photochromic dyes, which switch their fluorescence properties under light illumination.⁷ Most common representatives are derivatives of spiropyran,⁸ cyanine⁹⁻¹⁰ and some fluorescent proteins.¹¹⁻¹² The second approach is to couple a fluorescent dye with a non-fluorescent photochromic dye, that operate as a FRET pair.¹³ In this case, the photo-isomerization of the photochromic dyes modulates the FRET efficiency and thus switches on/off the dye fluorescence.¹⁴⁻¹⁵ This approach is more universal, as most of photochromic dyes are non-fluorescent and their combination with fluorescent dyes enables access to any desired emission color associated with high fluorescence quantum yield. Photoswitchable FRET-based molecules work very well as the distance within a typical molecular dyad is much less than the Förster radius required for an efficient FRET. On the other hand these systems present two limitations: (1) limited brightness of organic dyes and (2) multistep synthesis of the dyad, which makes these materials rather expensive. Both limitations could be overcome by the use of fluorescent nanoparticles (NPs). Indeed, they can be 10-100-fold as bright as organic dyes, which opens new possibilities in fluorescence bioimaging. Second, using straightforward protocols, they can be readily prepared with an appropriate photochromic dye to achieve FRET-based photoswitching. However, as the fluorescent particles are usually >5 nm large, the distance between the particle donor and the photochromic acceptor can exceed the Förster distance and thus decrease the FRET efficiency.

The most developed fluorescent NPs are quantum dots,¹⁶ dye-doped silica NPs¹⁷ and organic NPs.¹⁸⁻¹⁹ In the last decade, significant efforts have been made to make these NPs photoswitchable.²⁰ To achieve efficient switching, quantum dots were covered with multiple photochromic acceptors within the particle organic shell.²¹⁻²² However, it was found that the efficiency of switching despite optimized conditions remained modest (~2-fold). Examples in literature on dye-doped silica NPs showed better switching efficiency, compared to QDs, because in this case the photochromic acceptor could be encapsulated directly inside the particle core together with the dye donors.²³⁻²⁵ Within organic systems, photoresponsive polymer NPs

have already shown very promising results.²⁶⁻²⁷ This is notably the case of conjugated polymer NPs, which also can encapsulate photochromic dye directly inside the core.²⁸⁻³¹ In this case, the higher intensity variation (>10-fold) could be explained by fast energy transfer along the polymer conjugation, which ensures that the energy is efficiently transferred to long distances towards a single acceptor (i.e. photochromic dye).³²⁻³⁴ This phenomenon is called exciton diffusion and it is well known in sensors,³² light harvesting³⁵ and photovoltaic systems,³⁶ which rely on rapid communication within large ensemble of dyes to ensure efficient energy transfer.

Dye-doped polymer NPs are also very attractive organic systems, as they can be built from biodegradable eco-friendly materials and present exceptional brightness.³⁷⁻⁴⁰ However, only limited number of reports utilized FRET to obtain photoswitchable dve-doped polymer NPs.⁴¹⁻⁴⁴ One reason is that it is still a challenge to obtain dye-doped NPs with minimal self-quenching of the encapsulated dyes. Moreover, the problem of controlling FRET efficiency between the doped dyes and the photoswitch was rarely addressed.⁴³ In the present work, we hypothesized, that exciton diffusion, which is the reason for superguenching in the conjugated polymers, could be exploited to drive the photoswitching efficiency of dye-doped polymer NPs. To this end we selected our recently developed rhodamine doped NPs build from biodegradable polymer poly(D,L-lactide-co-glycolide) (PLGA).³⁸ Using hydrophobic perfluorinated counterion as an "insulator" between the cationic rhodamine dyes, we were able to prevent self-quenching at high dve loading. Unexpectedly, at high dve loading we observed for the first time a fluorescence blinking of 100-500 dyes encapsulated in one particle. This phenomenon was explained by the ultra-fast exciton diffusion, so that a single dark species (triplet or radical state of the dye) could quench the whole particle.³⁸ Remarkably, other counterions at the same dye loading did not show this behavior, so that the perfluorinated counterion was responsible for assembling rhodamine dyes in a close proximity to ensure the energy migration. Therefore, this system appeared promising for developing photoswitching NPs.

In the present work, we exploit the phenomenon of the exciton diffusion to build dye-doped polymer nanoparticles with excellent photoswitching ability. To this end, we co-encapsulated into PLGA NPs rhodamine B dye salt with perfluorinated counterion as well as a photochromic acceptor of the diarylethene family. To understand the role of the exciton diffusion, we prepared NPs with other counterions, which did not favor exciton diffusion of rhodamine dyes. It was found that with perfluorinated counterion light-driven variation of fluorescence intensity was up

to 20-fold, while for all other counterions, the switching efficiency was much lower. Thus, for the first time, we showed a direct connection between the collectiveness of the encapsulated dyes inside polymer NPs and their capacity to photoswitch. The performance of the new NPs was validated at the single particle level, where reversible photoswitching was demonstrated.

Nanoparticles studied in this work were prepared by nanoprecipitation of PLGA from acetonitrile. As we have shown earlier, diluted solutions of a polymer once precipitated in water can form NPs of 40-50 nm that are stabilized by the negative charge of carboxylate groups.^{38,45} To encapsulate a fluorophore and a photoswitch, they were simply added to the acetonitrile solution before the nanoprecipitation. As a fluorophore, we selected the octadecyl-rhodamine B (R18) bearing different counterions: inorganic perchlorate or tetraphenyl borates with different levels of fluorination (Scheme 1). As a photochromic dye, we selected the diphenylethene derivative **PCD1**, which was described earlier.⁴⁶ It is hydrophobic and thus should be efficiently encapsulated into polymer NPs, as shown for other low polar switches.⁴⁴ **PCD1** matches perfectly the optical properties of the donor dye R18, since its long-wavelength absorption band overlaps well with the emission of the donor (Fig. 1A). Moreover, the photoswitch can be selectively illuminated with 405 and 645 nm lasers, necessary for switching, without direct excitation of the R18 dye, which is important to prevent bleaching of the fluorophore during the photoswitching cycles.



Scheme 1. Chemical structure of the encapsulated fluorescent dye (R18) with different bulky counterions and the photochromic dye (PCD1). Schematic presentation of photoswitching

concept in dye-doped NPs. Small gray arrows show the exciton diffusion, while the large gray arrow presents FRET to a photochromic dye (brown).



Fig. 1. Spectroscopic properties of the R18 donor and the photochromic FRET acceptor PCD1, and photoswitching behavior of the latter in dioxane. (A) Absorption spectra of PCD1 at 0.02 mg/mL in dioxane in comparison to the normalized absorption and fluorescence spectra of R18 with F5-TPB counterion in PLGA NPs (1 wt% loading). Time-dependent absorbance of PCD1 at 630 nm under illumination at 405 nm (B) and 645 nm (C). (D) Absorbance of PCD1 at 630 nm under alternate illumination at 405 nm (\sim 1 mW/cm²) and 645 nm (\sim 200 mW/cm²).

We first studied a small volume (200 μ L) of the photochromic molecule PCD1 (0.02 mg/mL) in dioxane in 1 mL quartz cuvette, which was needed to irradiate the whole sample by a laser or a lamp of a fluorometer. To optimize conditions for photoswitching, the sample was illuminated at 405 nm by the lamp of the fluorometer with a light flux ~1 mW/cm² and by the defocused irradiation of a 645 nm laser with a light flux ~ 200 mW/cm². Illumination at 405 nm, resulted in the rapid growth of the absorbance at 630 nm, which reached saturation after ~2 min (Fig. 1B). These changes indicated the formation of the closed (colored B) form of the photoswitch. In contrast, to switch the molecule back to the open (colorless A) form, an irradiation of the sample at 645 nm for at least 20 min with much higher power was required (Fig. 1C). The observation of absorption peaks at 630 nm under alternate irradiation confirmed the reversibility of the photochromic isomerization without fatigue for at least 5 complete cycles (Fig. 1D).

To investigate the photoisomerization conditions inside PLGA polymer NPs we encapsulated 1 wt% of the photochromic dye with respect to the mass of polymer and performed the same cycles of irradiation. To obtain full photoisomerization inside PLGA, we increased the time of irradiation at 405 nm up to 10 min and at 645 nm up to 40 min. (Fig. S1).



Fig. 2. Switching properties of the dye-doped PLGA NPs as a function of counterion and dye loading in PLGA NPs. (A) Variation of relative peak intensity under alternate irradiation of PLGA NPs loaded with 1 wt% of rhodamine R18 with different counterions and 0.3 wt% of photochromic dye PCD1. (B) Variation of relative peak intensity under alternate irradiation of PLGA NPs loaded with 0.1 - 3 wt% of R18/F5-TPB and 0.3 wt% of PCD1. Excitation wavelength was 520 nm.

Next, the photochromic dye PCD1 was co-encapsulated in PLGA NPs together with R18 dye bearing four different counterions: perchlorate (ClO₄), TPB, F1-TPB, F5-TPB. Dynamic light scattering (DLS) showed that the particle size remained in the range 42-47 nm (polydispersity index ~0.1) for most of formulations of R18 salts with or without PCD1 switch (Table S1). The only exception was NPs with R18/ClO₄ salt, which, in line with our earlier works, produced larger NPs.³⁸ The emission of the obtained NPs was further studied under illumination cycles as it was established above in model conditions. We called off state the state of NPs where the photochromic dye in closed form behaves as an energy acceptor for rhodamine B, and, on state the opposite state without FRET. To characterize the system, we determined two parameters: the *relative intensity* = I / I_0^{off} and *switching efficiency* = I_{on}/I_{off} , where *I* is the peak fluorescence intensity at a given condition; I_0^{off} are the peak fluorescence intensity at the off states,

respectively at a given illumination cycle. First, we verified for the most promising R18 salt with F5-TPB counterion the optimal concentration of the photochromic dye inside NPs. For 1 wt% loading of R18/F5-TPB dye, the switching efficiency grew up to 0.3 wt% of the photoswitch, while for 0.5 wt% the switching was already less efficient (Fig. S2). The presence of 1 wt% of the fluorophore did not have any influence on the photoswitch fatigue (Fig. S3), whereas the presence of 0.3 wt% of photoswitch did not influence the photostability of the fluorophore (Fig. S4). Therefore, in all our further studies we used systematically 0.3 wt% of the photoswitch. We found that all NPs bearing one of the four different R18 salts were able to photo-switch their fluorescence, though the switching efficiency depended clearly on the nature of the counterion. Indeed, while for perfluorinated counterion F5-TPB, the switching efficiency was around 15, for all other counterions it was only 2-4 (Fig. 2A). The calculated Förster radius for a pair R18 and PCD1 was 2.1 and 4.9 nm for the open and closed forms of the switch, respectively. Assuming a homogeneous distribution of the PCD1 acceptors inside NPs, a volume taken by one acceptor was 240 nm³, which gave an average distance between the acceptors of 7.7 nm. Theoretically, the closest average distance between R18 donor and PCD1 acceptors was 4.7 nm when R18 was located in the center of tetrahedron formed by PCD1 (hexagonal arrangement of PCD1 separated by 7.7 nm). In this case, one R18 donor was surrounded with four acceptors, so that using FRET model for multiple (four) acceptors,⁴⁷ the estimated FRET efficiency was 3.1 and 84% for open and closed forms of PCD1, respectively. Thus, FRET can at least in part explain the switching behavior of our NPs. However, we should not exclude the electron transfer between R18 and the closed form of PCD1. Knowing the reduction and oxidation potentials of rhodamine B (-0.8 and 1.2 V, respectively)⁴⁸ and using the Rehm-Weller formalism,⁴⁹ the estimated reduction and oxidation potentials of this dye in the excited state were +1.38 and -0.98 V (vs SCE), respectively. For the switch, the redox data are available only for an analogue of PCD1 in the closed form with the oxidation and reduction potentials of +1.45 and -1.11 V (vs SCE), respectively.⁵⁰ The value of the oxidation potential of the model switch is close to the reduction potential of rhodamine B in the excited state, which (after neglecting small columbic effects) suggests that the electron transfer could take place from PCD1 to R18. In any case, the estimated FRET efficiency for the closed form is in line with the experimental data for all counterions, except F5-TPB (Fig. 3A). For the latter, the FRET efficiency was much higher, so that the off state in these NPs was ~12-fold less fluorescent than theoretically predicted. This is an indication

that counterion plays a particular role in the organization of R18 dyes. As we hypothesized earlier³⁸ F5-TPB could bring the donors close to each other thus favoring exciton diffusion, which could boost the FRET efficiency.

To verify whether this effect of F5-TPB is linked with the exciton diffusion process, we measured the steady-state fluorescence anisotropy of NPs with all four counterions. When the energy migrates within encapsulated fluorophores that are randomly orientated inside the polymer matrix, the fluorescence anisotropy rapidly decreases after each step of the energy hopping between dyes.⁵¹⁻⁵² As the fluorophores are confined within the rigid polymer matrix, the loss of fluorescence anisotropy in this system could be mainly attributed to the exciton diffusion process. In line with our earlier study,³⁸ NPs loaded with R18/F5-TPB salt presented much lower fluorescence anisotropy than all other salts, indicating that the most efficient exciton migration was achieved with this salt (Fig. 3B). According to our previous time-resolved anisotropy data at 1 wt% R18/F5-TPB loading, corresponding to ~100 dyes per particle, at least 40 dyes were involved in the exciton diffusion.³⁸ These results correlated well the much higher efficiency of the photoswitching observed for R18/F5-TPB NPs (Fig. 3A). The unique behavior of F5-TPB is probably related to its perfluorination, which may favor assembly of R18 dyes with short interfluorophore distances inside polymer matrix allowing fast exciton diffusion. The role of fluorines could be related to so-called fluorous effect (or super-hydrophobicity)⁵³ as well as to their strong electronegativity that shifts the negative charge of F5-TPB to its periphery. To further check the importance of the exciton diffusion on the photoswitching efficiency, we varied the concentration of the fluorescent donor dyes (R18/F5-TPB), while keeping the photoswitch concentration constant. In the case of non-communicating donors, the FRET efficiency, i.e. photoswitching efficiency, should be independent on the concentration of the donors.⁵⁴ However, we observed clearly that the photoswitching efficiency increased dramatically on increasing the donor dye concentration (Fig 2B, Fig. 3A). Moreover, this increase correlated perfectly with the decrease in the fluorescence anisotropy (Fig. 3B), indicating faster rates of the exciton diffusion for higher dye loading. Indeed, at higher dye loading the distance between the donor (R18) dyes should decrease, which should lead to faster energy hopping, as we showed earlier using timeresolved anisotropy and fluorescence blinking experiments.³⁸ The present data suggest that the energy transfer to the photoswitch can be drastically improved by exploiting the exciton diffusion within the donor dyes. To the best of our knowledge, it is the first time that a

connection between the photoswitching efficiency and the exciton diffusion was established for dye-doped nanoparticles.



Fig. 3. Correlation between photoswitching efficiency of NPs and fluorescence anisotropy of the encapsulated dyes. (A) Average switching efficiency (I_{on}/I_{off}) within four complete on/off cycles for dye-doped NPs containing 0.3 wt% of PCD1, with different counterions and at different R18/F5-TPB dye loading. The values given in this panel present the FRET efficiency (%) for the off state calculated from I_{off} and the intensity of NPs without PCD1. (B) Fluorescence anisotropy of the encapsulated dyes for the same NPs samples but without PCD1.

Finally, we evaluated the performance of our NPs at the single-particle level using wide-field fluorescence microscopy. To this end, we immobilized fluorescent NPs containing 1 wt% R18/F5-TPB and 0.3 wt% of PCD1 at the glass surface covered with positively charged polymer PEI. Then, under the fluorescence microscope, we illuminated the observation region with alternated blue (405 nm) and red (645 nm) lasers and recorded the fluorescence image after each illumination step. We found that after illumination at 645 nm, the particles appeared bright and were well seen on the images (Fig. 4A). In contrast, after 405 nm illumination, most of the particles became dim, indicating that they underwent photo-conversion into the off state. The average intensity variation showed a clear alternation of the particle intensity (Fig. 4B). However, we should note that the value of the average intensity variation was lower than in

solution. This is in line with other studies of NPs switching showing that at the single particle level the switching appears less efficient.⁵⁵ There can be multiple factors, particularly related to the use of much higher illumination power under the microscope. The higher powers could bleach the encapsulated R18 dyes or the photoswitch and thus decrease the switching efficiency. Another reason is that at the single particle level, the signal to noise ratio is significantly lower than for NPs in solution, where a large population is simultaneously excited. Therefore, the absolute changes under the microscope could be decreased by the background noise. The other issue is the observed heterogeneity in the switching efficiency. While some particles showed switching efficiency reaching 30, for others it was below the average (Fig. S5). This heterogeneity is related to inhomogeneity in the dye and photoswitch doping, particle size, etc. Therefore, an important challenge in the future will be to improve the homogeneity in the particle switching efficiency.



Fig. 4. Single-particle observation of photoswitching of dye-doped NPs. (A) Wide field images of NPs containing 1 wt% R18/F5-TPB and 0.3 wt% of PCD1 after illumination at 405 (upper panels) and 645 nm (lower panels). (B) Average relative intensity (I / I_0^{off}) of NPs in the on and off state obtained from these images. The optimal conditions for photoswitching were 60 s illumination at 645 nm with laser power 97 W/cm², and 5 s illumination at 405 nm with laser power 8.7 W/cm². To record fluorescence images the power of the laser at 532 was set to 0.2 W/cm².

In the present work, we propose for the first time to utilize exciton diffusion within the encapsulated fluorophores to achieve efficient photoswitching. To this end, we utilized our recently proposed concept of hydrophobic counterion for encapsulating a cationic dye (octadecyl

rhodamine B) into NPs. This counterion serves as insulator that prevents dye self-quenching but at the same time assembles the dyes in close proximity to ensure fast dye-dye communication inside a polymer matrix. We showed that only the perfluorinated tetraphenylborate counterion favoring the exciton diffusion enables efficient photoswitching efficiency (~20) of NPs in suspensions. For other counterions, where the inter-fluorophore communication was less pronounced, the photoswitching efficiency was much lower. Wide-field fluorescence microscopy studies confirmed the photoswitching of our NPs at the single-particle level. Our study shows that exciton diffusion within fluorophores inside NPs can ensure efficient FRET to photoswitch producing highly efficient photoswitching. The proposed concept paves the way to new efficient photoswitchable nanomaterials.

ACKNOWLEDGMENT

K.T. was supported by a fellowship from the Ministère de la Recherche. The work was supported by University of Strasburg (IdEX 2015, W15RAT68) and CNRS.

SUPPORTING INFORMATION

Detailed experimental section, and some additional optical spectroscopy and microscopy data. This material is available free of charge via the Internet at http://pubs.acs.org.

REFERENCES

(1) Fernandez-Suarez, M.; Ting, A. Y. Fluorescent Probes for Super-Resolution Imaging in Living Cells. *Nat. Rev. Mol. Cell Biol.* **2008**, *9*, 929-943.

(2) Bates, M.; Huang, B.; Dempsey, G. T.; Zhuang, X. Multicolor Super-Resolution Imaging with Photo-Switchable Fluorescent Probes. *Science* **2007**, *317*, 1749-1753.

(3) Heilemann, M.; Dedecker, P.; Hofkens, J.; Sauer, M. Photoswitches: Key Molecules for Subdiffraction-Resolution Fluorescence Imaging and Molecular Quantification. *Laser Photon. Rev.* **2009**, *3*, 180-202.

(4) Tian, Z.; Li, A. D. Photoswitching-Enabled Novel Optical Imaging: Innovative Solutions for Real-World Challenges in Fluorescence Detections. *Acc. Chem. Res.* **2013**, *46*, 269-279.

(5) van de Linde, S.; Sauer, M. How to Switch a Fluorophore: From Undesired Blinking to Controlled Photoswitching. *Chem. Soc. Rev.* **2014**, *43*, 1076-1087.

(6) Irie, M. Diarylethenes for Memories and Switches. Chem. Rev. 2000, 100, 1685-1716.

(7) Pang, S. C.; Hyun, H.; Lee, S.; Jang, D.; Lee, M. J.; Kang, S. H.; H., A. K. Photoswitchable Fluorescent Diarylethene in a Turn-on Mode for Live Cell Imaging. *Chem. Commun.* **2012**, *48*, 3745-3747.

(8) Klajn, R. Spiropyran-Based Dynamic Materials. Chem. Soc. Rev. 2014, 43, 148-184.

(9) Heilemann, M.; Margeat, E.; Kasper, R.; Sauer, M.; Tinnefeld, P. Carbocyanine Dyes as Efficient Reversible Single-Molecule Optical Switch. *J. Am. Chem. Soc.* **2005**, *127*, 3801-3806.

(10) Bates, M.; Blosser, T. R.; Zhuang, X. W. Short-Range Spectroscopic Ruler Based on a Single-Molecule Optical Switch. *Phys. Rev. Lett.* **2005**, *94*, 108101.

(11) Habuchi, S.; Ando, R.; Dedecker, P.; Verheijen, W.; Mizuno, H.; Miyawaki, A.; Hofkens, J. Reversible Single-Molecule Photoswitching in the Gfp-Like Fluorescent Protein Dronpa. *Proc. Natl. Acad. Sci. U.S.A.* **2005**, *102*, 9511-9516.

(12) Ando, R.; Mizuno, H.; Miyawaki, A. Regulated Fast Nucleocytoplasmic Shuttling Observed by Reversible Protein Highlighting. *Science* **2004**, *306*, 1370-1373.

(13) Sapsford, K. E.; Berti, L.; Medintz, I. L. Materials for Fluorescence Resonance Energy Transfer Analysis: Beyond Traditional Donor-Acceptor Combinations. *Angew. Chem. Int. Ed. Engl.* **2006**, *45*, 4562-4588.

(14) Raymo, F. M.; Tomasulo, M. Electron and Energy Transfer Modulation with Photochromic Switches. *Chem. Soc. Rev.* **2005**, *34*, 327-336.

(15) Ouhenia-Ouadahi, K.; Metivier, R.; Maisonneuve, S.; Jacquart, A.; Xie, J.; Leaustic, A.; Yu, P.; Nakatani, K. Fluorescence Photoswitching and Photoreversible Two-Way Energy Transfer in a Photochrome-Fluorophore Dyad. *Photochem. Photobiol. Sci.* **2012**, *11*, 1705-1714.

(16) Alivisatos, A. P. Semiconductor Clusters, Nanocrystals, and Quantum Dots. *Science* **1996**, *271*, 933-937.

(17) Bonacchi, S.; Genovese, D.; Juris, R.; Montalti, M.; Prodi, L.; Rampazzo, E.; Zaccheroni, N. Luminescent Silica Nanoparticles: Extending the Frontiers of Brightness. *Angew. Chem. Int. Ed. Engl.* **2011**, *50*, 4056-4066.

(18) Kaeser, A.; Schenning, A. P. H. J. Fluorescent Nanoparticles Based on Self-Assembled Pi-Conjugated Systems. *Adv. Mater.* **2010**, *22*, 2985-2997.

(19) Li, K.; Liu, B. Polymer-Encapsulated Organic Nanoparticles for Fluorescence and Photoacoustic Imaging. *Chem. Soc. Rev.* **2014**, *43*, 6570-6597.

(20) Tian, Z.; Wu, W.; Li, A. D. Photoswitchable Fluorescent Nanoparticles: Preparation, Properties and Applications. *ChemPhysChem* **2009**, *10*, 2577-2591.

(21) Diaz, S. A.; Menendez, G. O.; Etchehon, M. H.; Giordano, L.; Jovin, T. M.; Jares-Erijman, E. A. Photoswitchable Water-Soluble Quantum Dots: Pcfret Based on Amphiphilic Photochromic Polymer Coating. *ACS Nano* **2011**, *5*, 2795-2805.

(22) Medintz, I. L.; Trammell, S. A.; Mattoussi, H.; Mauro, J. M. Reversible Modulation of Quantum Dot Photoluminescence Using a Protein-Bound Photochromic Fluorescence Resonance Energy Transfer Acceptor. *J. Am. Chem. Soc.* **2004**, *126*, 30-31.

(23) Genovese, D.; Montalti, M.; Prodi, L.; Rampazzo, E.; Zaccheroni, N.; Tosic, O.; Altenhoner, K.; May, F.; Mattay, J. Reversible Photoswitching of Dye-Doped Core-Shell Nanoparticles. *Chem. Commun.* **2011**, *47*, 10975-10977.

(24) May, F.; Peter, M.; Hutten, A.; Prodi, L.; Mattay, J. Synthesis and Characterization of Photoswitchable Fluorescent Sio2 Nanoparticles. *Chemistry* **2012**, *18*, 814-821.

(25) Folling, J.; Polyakova, S.; Belov, V.; van Blaaderen, A.; Bossi, M. l.; Hell, S. W. Synthesis and Characterization of Photoswitchable Fluorescent Silica Nanoparticles. *Small* **2008**, *4*, 134-142.

(26) Swaminathan, S.; Garcia-Amoros, J.; Fraix, A.; Kandoth, N.; Sortino, S.; Raymo, F. M. Photoresponsive Polymer Nanocarriers with Multifunctional Cargo. *Chem. Soc. Rev.* **2014**, *43*, 4167-4178.

(27) Li, C.; Liu, S. Polymeric Assemblies and Nanoparticles with Stimuli-Responsive Fluorescence Emission Characteristics. *Chem. Commun.* **2012**, *48*, 3262-3278.

(28) Harbron, E. J. Fluorescence Intensity Modulation in Photochromic Conjugated Polymer Systems. *Isr. J. Chem.* **2013**, *53*, 256-266.

(29) Chan, Y. H.; Gallina, M. E.; Zhang, X.; Wu, I. C.; Jin, Y.; Sun, W.; Chiu, D. T. Reversible Photoswitching of Spiropyran-Conjugated Semiconducting Polymer Dots. *Anal. Chem.* **2012**, *84*, 9431-9438.

(30) Feng, G.; Ding, D.; Li, K.; Liu, J.; Liu, B. Reversible Photoswitching Conjugated Polymer Nanoparticles for Cell and Ex Vivo Tumor Imaging. *Nanoscale* **2014**, *6*, 4141-4147.

(31) Osakada, Y.; Hanson, L.; Cui, B. Diarylethene Doped Biocompatible Polymer Dots for Fluorescence Switching. *Chem. Commun.* **2012**, *48*, 3285-3287.

(32) Thomas Iii, S. W.; Joly, G. D.; Swager, T. M. Chemical Sensors Based on Amplifying Fluorescent Conjugated Polymers. *Chem. Rev.* 2007, *107*, 1339-1386.

(33) Achyuthan, K. E.; Bergstedt, T. S.; Chen, L.; Jones, R. M.; Kumaraswamy, S.; Kushon, S. A.; Ley, K. D.; Lu, L.; McBranch, D.; Mukundan, H.; Rininsland, F.; Shi, X.; Xia, W.; Whitten, D. G. Fluorescence Superquenching of Conjugated Polyelectrolytes: Applications for Biosensing and Drug Discovery. *J. Mater. Chem.* **2005**, *15*, 2648-2656.

(34) Wang, X. L.; Groff, L. C.; McNeill, J. D. Multiple Energy Transfer Dynamics in Blended Conjugated Polymer Nanoparticles. *J. Phys. Chem. C* **2014**, *118*, 25731-25739.

(35) Bopp, M. A.; Sytnik, A.; Howard, T. D.; Cogdell, R. J.; Hochstrasser, R. M. The Dynamics of Structural Deformations of Immobilized Single Light-Harvesting Complexes. *Proc. Natl. Acad. Sci. U.S.A.* **1999**, *96*, 11271-11276.

(36) Menke, S. M.; Luhman, W. A.; Holmes, R. J. Tailored Exciton Diffusion in Organic Photovoltaic Cells for Enhanced Power Conversion Efficiency. *Nat. Mater.* **2013**, *12*, 152-157.

(37) Trofymchuk, K.; Reisch, A.; Shulov, I.; Mely, Y.; Klymchenko, A. S. Tuning the Color and Photostability of Perylene Diimides inside Polymer Nanoparticles: Towards Biodegradable Substitutes of Quantum Dots. *Nanoscale* **2014**, *6*, 12934-12942.

(38) Reisch, A.; Didier, P.; Richert, L.; Oncul, S.; Arntz, Y.; Mely, Y.; Klymchenko, A. S. Collective Fluorescence Switching of Counterion-Assembled Dyes in Polymer Nanoparticles. *Nat. Commun.* **2014**, *5*, 4089.

(39) Wagh, A.; Qian, S. Y.; Law, B. Development of Biocompatible Polymeric Nanoparticles for in Vivo Nir and Fret Imaging. *Bioconjug. Chem.* **2012**, *23*, 981-992.

(40) Wagh, A.; Jyoti, F.; Mallik, S.; Qian, S.; Leclerc, E.; Law, B. Polymeric Nanoparticles with Sequential and Multiple Fret Cascade Mechanisms for Multicolor and Multiplexed Imaging. *Small* **2013**, *9*, 2129-2139.

(41) Zhu, M. Q.; Zhu, L.; Han, J. J.; Wu, W.; Hurst, J. K.; Li, A. D. Spiropyran-Based Photochromic Polymer Nanoparticles with Optically Switchable Luminescence. *J. Am. Chem. Soc.* **2006**, *128*, 4303-4309.

(42) Chen, J.; Zhang, P.; Fang, G.; Weng, C.; Hu, J.; Yi, P.; Yu, X.; Li, X. One-Pot Synthesis of Amphiphilic Reversible Photoswitchable Fluorescent Nanoparticles and Their Fluorescence Modulation Properties. *Polym. Chem.* **2012**, *3*, 685-693.

(43) Chen, J.; Zeng, F.; Wu, S. Construction of Energy Transfer Systems within Nanosized Polymer Micelles and Their Fluorescence Modulation Properties. *ChemPhysChem* **2010**, *11*, 1036-1043.

(44) Yildiz, I.; Impellizzeri, S.; Deniz, E.; McCaughan, B.; Callan, J. F.; Raymo, F. M. Supramolecular Strategies to Construct Biocompatible and Photoswitchable Fluorescent Assemblies. *J. Am. Chem. Soc.* **2011**, *133*, 871-879.

(45) Reisch, A.; Runser, A.; Arntz, Y.; Mély, Y.; Klymchenko, A. S. Charge-Controlled Nanoprecipitation as a Modular Approach to Ultrasmall Polymer Nanocarriers: Making Bright and Stable Nanoparticles. *ACS Nano* **2015**, DOI: 10.1021/acsnano.1025b00214.

(46) Altenhoener, K.; Lamm, J.-H.; Mattay, J. Novel Dithienylethenes with Extended Pi-Systems: Synthesis by Aldol Condensation and Photochromic Properties. *Eur. J. Org. Chem.* **2010**, 6033-6037.

(47) Fabian, A. I.; Rente, T.; Szoellosi, J.; Matyus, L.; Jenei, A. Strength in Numbers: Effects of Acceptor Abundance on Fret Efficiency. *ChemPhysChem* **2010**, *11*, 3713-3721.

(48) Valenti, G.; Rampazzo, E.; Bonacchi, S.; Khajvand, T.; Juris, R.; Montalti, M.; Marcaccio, M.; Paolucci, F.; Prodi, L. A Versatile Strategy for Tuning the Color of Electrochemiluminescence Using Silica Nanoparticles. *Chem. Commun.* **2012**, *48*, 4187-4189.

(49) Rehm, D.; Weller, A. Kinetics of Fluorescence Quenching by Electron and H-Atom Transfer. *Isr. J. Chem.* **1970**, *8*, 259–271.

(50) Berberich, M.; Wuerthner, F. Tuning the Redox Properties of Photochromic Diarylethenes by Introducing Electron-Withdrawing Substituents. *Asian J. Org. Chem.* **2013**, *2*, 250-256.

(51) Colby, K. A.; Burdett, J. J.; Frisbee, R. F.; Zhu, L.; Dillon, R. J.; Bardeen, C. J. Electronic Energy Migration on Different Time Scales: Concentration Dependence of the Time-Resolved Anisotropy and Fluorescence Quenching of Lumogen Red in Poly(Methyl Methacrylate). *J. Phys. Chem. A* **2010**, *114*, 3471-3482.

(52) Yeow, E. K. L.; Ghiggino, K. P.; Reek, J. N. H.; Crossley, M. J.; Bosman, A. W.; Schenning, A.; Meijer, E. W. The Dynamics of Electronic Energy Transfer in Novel Multiporphyrin Functionalized Dendrimers: A Time-Resolved Fluorescence Anisotropy. *J. Phys. Chem. B* **2000**, *104*, 2596-2606.

(53) Cametti, M.; Crousse, B.; Metrangolo, P.; Milani, R.; Resnati, G. The Fluorous Effect in Biomolecular Applications. *Chem. Soc. Rev.* **2012**, *41*, 31-42.

(54) Genovese, D.; Rampazzo, E.; Bonacchi, S.; Montalti, M.; Zaccheroni, N.; Prodi, L. Energy Transfer Processes in Dye-Doped Nanostructures Yield Cooperative and Versatile Fluorescent Probes. *Nanoscale* **2014**, *6*, 3022-3036.

(55) Davis, C. M.; Childress, E. S.; Harbron, E. J. Ensemble and Single-Particle Fluorescence Photomodulation in Diarylethene-Doped Conjugated Polymer Nanoparticles. *J. Phys. Chem. C* **2011**, *115*, 19065-19073.