

Alma Mater Studiorum Università di Bologna Archivio istituzionale della ricerca

Effects of powders and process parameters on density and hardness of A357 aluminum alloy fabricated by selective laser melting

This is the final peer-reviewed author's accepted manuscript (postprint) of the following publication:

Published Version:

Effects of powders and process parameters on density and hardness of A357 aluminum alloy fabricated by selective laser melting / Tonelli L.; Liverani E.; Valli G.; Fortunato A.; Ceschini L. - In: INTERNATIONAL JOURNAL, ADVANCED MANUFACTURING TECHNOLOGY. - ISSN 0268-3768. - STAMPA. - 106:(2020), pp. 371-383. [10.1007/s00170-019-04641-x]

Availability:

This version is available at: https://hdl.handle.net/11585/712454 since: 2024-04-22

Published:

DOI: http://doi.org/10.1007/s00170-019-04641-x

Terms of use:

Some rights reserved. The terms and conditions for the reuse of this version of the manuscript are specified in the publishing policy. For all terms of use and more information see the publisher's website.

This item was downloaded from IRIS Università di Bologna (https://cris.unibo.it/). When citing, please refer to the published version.

Effects of powders and process parameters on density and hardness of A357 aluminum alloy fabricated by Selective Laser Melting

Lavinia Tonelli^{(1)*}, Erica Liverani⁽²⁾, Giuseppe Valli⁽¹⁾, Alessandro Fortunato⁽¹⁾, Lorella Ceschini⁽³⁾

 ⁽¹⁾ Department of Industrial Engineering (DIN), Alma Mater Studiorum - University of Bologna, Bologna (Italy)
 ⁽²⁾ Interdepartmental Center for Industrial Research - Advanced Applications in Mechanical Engineering and Materials Technology (CIRI – MAM), Alma Mater Studiorum - University of Bologna, Bologna (Italy)
 ⁽³⁾ Department of Civil, Chemical, Environmental and Materials Engineering (DICAM), Alma Mater Studiorum -University of Bologna, Bologna (Italy)

*corresponding author: lavinia.tonelli2@unibo.it, lavinia.tonelli@gmail.com Department of Industrial Engineering – University of Bologna Viale Risorgimento 4, 40136 Bologna (Italy) Tel +39 0512093465 Fax +39 0512093467

Abstract

Additive Manufacturing processes based on the local fusion of a powder bed, such as Selective Laser Melting (SLM), are a valid alternative to conventional technologies and a growing number of industrial sectors are currently relying on these processes for the production of different components. However, there are still some limits in using SLM and they are often related to the feedstock material. For this reason, in the present work the effects of powders properties and pre-treatments, as well as process parameters, on the fabrication of aluminum alloy A357 samples were investigated. Two different batches of powder were considered in order to evaluate the effects of particles shape and size in the as-received condition and after two different pre-treatments: 60°C for 3 hours and 200°C for 1 hour. Selective laser melted samples were produced in the conditions described above and were then characterized in terms of density, phase and chemical composition, defects and hardness.

The results showed a correlation between powder conditions in terms of morphology and pretreatment on the properties of SLM A357 aluminum alloy components.

Keywords

Aluminum alloy; Selective Laser Melting; Pre-treatment; Powder feedstock; Additive Manufacturing

1. Introduction

Currently, Selective Laser Melting (SLM) is the most used metal powder bed additive process since it is a valid solution for the production of various and different components. A growing number of research groups are working on the development and the optimization of SLM and the literature shows vast opportunities to exploit the potential of this process. Several works addressed the problem of optimizing process parameters, both from a technological [1-3] and a metallurgical [4-6] point of view. These papers demonstrated that it is possible to reach near-full densities and good mechanical properties using SLM. Furthermore, the research topics concerning aspects related to residual stresses [7,8] and the need of post-processes [9-11], have proposed several useful solutions.

Many of the outcomes mentioned above are probably linked to the feedstock. The presence of porosity in SLM builds, in fact, is not always caused by un-optimized process parameters, but can also be related to the presence of porosities in the initial batch of powder due to trapped atomization gas [12]. Moreover, pores in SLM components can result from non-spherical geometry and from the presence of attached "satellites" on main powder grains that compromise the packing capacity of the powder bed and prevent the correct deposition of the layer [13]. Powder properties such as flowability and packing density are also influenced by the particles size distribution and both are strictly related to the final properties of SLM production. Several authors have demonstrated that powder has to achieve good random close packing, therefore a mixture of both large and small particles is needed, since the presence of fine particles allows filling the voids between the coarser ones [14-16]. Nevertheless, if the particles size distribution is too wide, the laser power is unable to melt the largest particles or might over-melt the small ones, leading to un-melted regions, spatter and balling effects [17]. Furthermore, particles finer than ~10 µm favor cohesion, thus increasing powder agglomeration, and consequently decrease the flowability, resulting in a non-uniform powder bed [18,19]. Moreover, the surface of aluminum powders reacts with oxygen to form a passivation aluminum oxide layer that absorbs humidity. A large number of fine particles increases the surface area in contact with air and thus the amount of adsorbed water, which compromises the powder flow [20]. According to Herbert [21], the metallurgy of powder bed fusion technologies is strongly influenced by the feedstock quality: water absorption, formation of oxides and hydroxides layers can negatively affect not only the powder flowability, but also the melting and solidification processes. In case of oxides layer covering powder particles, for example, most of the laser beam heating is absorbed by the layer, since it requires high

temperature to undergo melting. In addition, due to the low specific heat capacity of oxides, also heat conduction is reduced. Furthermore, water absorption can be detrimental for flowability of the powders, thus compromising the proper spreading of particles, but it may also lead to changes in the chemical composition, as a consequence of the hydrogen dissociation [21, 22]. So, powder pre-treatments and proper storage solutions have to be considered.

Many of the considerations above can be extended also to the recycled powder, but in that case the experiments led to different results. It is well known that over-heated powders increase dimensions and change their morphology and rheology behavior. However, some authors have shown that sieving allows to separate these grains form the other and obtain a recycled powder very similar to the initial feedstock [23]; while other papers stated the opposite [24].

The state of art gives a wide overview of the rheological properties of powder affecting the SLM process for several alloys regularly used. However, these data are not yet sufficient to completely understand the effects of the raw material on the final properties of the components [22]. The main reason is that powders are strongly influenced by the storage and handling conditions and they are not always maintained in a controlled humidity and temperature environment. Therefore, the storage condition must be examined and possible solutions to re-establish the as-received properties of powders must be carried out. In particular, aluminum alloys can easily react with air oxygen and aluminum powders are strongly influenced by the first to deal with these aspects, but considering only one initial condition, both in terms of type of powder and the possible thermal treatment to perform before process. In a recent work, Muñiz-Lerma et al. [20] performed a comprehensive characterization of A356 and A357 powders for Additive Manufacturing (AM) subjected to a 200°C pre-treatment, and they even propose interesting and non-traditional techniques to determine powders properties. However, they did not correlate the powder properties to the resulting samples.

In this work, the authors have chosen to enrich the knowledge about the effect of powders properties and pre-treatments, as well as process parameters, on the fabrication of aluminum SLM samples. In this view, two different virgin A357 powders were considered, nominally with the same chemical composition and supplied by the same manufacturer, but obtained with different processes. On both the powders, the effect of two preliminary treatments that could eliminate the humidity effect due to an uncontrolled storage, was evaluated. SLM samples were fabricated by using the two powders, subjected to the different pre-treatments, and by varying the process parameters, in order to correlate final properties of samples to both the process conditions and the quality of the powder feedstock. In particular, the authors have analyzed the

mutual effects of the described factors, as follows: i) influence of pre-treatment on powder morphology; ii) influence of powder morphology (axis major and aspect ratio) on samples density and hardness; iii) influence of pre-treatment temperature and soaking time on samples density and hardness; iv) influence of process parameters (laser power and scan speed) on final samples density, hardness and defects.

2. Experimental Procedure

In the present study, two different gas atomized powders of the A357 aluminum alloy (Aluminum Association designation [26]) were considered for the production of AM samples. Both powders were produced by the same supplier (LPW Carpenter Additive, Carpenter Technology Corporation, USA) adopting two different processes, whose details cannot be disclosed since they represent industrial sensitive information. Powders belonging to the two sets will be referred to as Powder L and Powder H hereafter. Basing on the data provided by the supplier, reported in Table 1 for chemical composition and Table 2 for other powder properties, they mainly differ in the Mg and N content, higher in Powder H than Powder L, and in powder properties, such as flowability and apparent density. The latter properties, in particular, were not provided for Powder L since, in this case, particles tend not to flow at all.

Table 1: Chemical composition (wt.%) of powders, given by the supplier [27]

	AI	Si	Mg	Fe	Cu	Mn	Ti	Zn	0	Ν	Other
Powder L	Bal.	6.96	0.49	0.10	0.01	< 0.01	0.09	< 0.01	0.1	< 0.001	< 0.15
Powder H	Bal.	6.90	0.55	0.09	< 0.05	< 0.01	0.09	< 0.01	0.1	<0.2	< 0.1

Table 2: Powders properties, given by the supplier [27]

	Laser Size Diffraction [µm] (ASTM B822)			Sieve Analysis (wt.%)	Carney Flow [s/75g] (ASTM B213)	Apparent Density [g/cm ³] (ASTM B212)
	DV(10)	DV(50)	DV(90)	+ 63 µm	-	-
Powder L	19.8	40.4	73.2	0	-	-
Powder H	26.0	40.0	62.0	0	38.25	1.3

2.1 Fabrication of SLM samples

A preliminary experimental campaign was carried out by producing samples with powders in the as-received condition, however, in the reason of the poor flowability ascribable to the high humidity content, results were unsatisfactory. So, both powder H and L were subjected to a drying pre-treatment, with the aim to reduce the adsorbed humidity. Two kind of heat-treatments were investigated: a high temperature drying and a low temperature one. The first heat treatment consisted of heating the powder up to 60°C and soaking for 3h, the second one of heating up to 200°C and soaking for 1 h.

In both cases the heat treatment was carried out in a muffle furnace, in ambient atmosphere, using a heating ramp of 100 °C/h and an air cooling.

All samples were built in a SLM machine, (MYSINT100 RM manufactured by SISMA) equipped with a 200 W fiber laser source with a spot diameter of 55 μ m. Melting process was carried out in a nitrogen environment with a residual oxygen content of 0.1 vol.%.

Process parameters, like building orientation, supports generation, laser power, scanning velocity and strategy, were defined using the Autofab software by Materialise.

A roto-translating 3 x 3 mm² chessboard was used for scanning the bulk volume of each sample. The distance between laser tracks (hatch distance) inside the chessboard was fixed at 70 μ m and the layer thickness was set at 20 μ m. Building direction was chosen as vertical and the samples (with dimensions 10 x 10 x 15 mm³) were randomly distributed in the building plate. In order to compare the two different type of powders and the two different powders pretreatments, a total of four set of samples were realized with the process parameters shown in Table 3.

Energy density Laser Power Scan velocity [mm/s] [J/mm³] [W] 70 500; 700; 900; 1200 100 - 41.790 500; 700; 900; 1200 128.6 - 53.6 110 500; 700; 900; 1200 157.1 – 65.5 500; 700; 900; 1200 130 185.7 – 77.4 150 500; 700; 900; 1200 214.3 - 89.3170 500; 700; 900; 1200 242.9 - 101.2

Table 3: Process parameters adopted for the fabrication of SLM samples

2.2 Powders characterization

Free surfaces and cross-sections of powders were analyzed in the as-received condition and after pre-treatment (soaking at 200°C for 1h and at 60°C for 3h) by means of a Scanning Electron Microscopy with Energy Dispersive X-Ray Spectroscopy (SEM-EDS, Zeiss EVO 50). Particles characterization, in terms of size distribution and aspect ratio, was carried out on SEM micrographs of free powders via image analysis, using the ImageJ open source software [28]. X-ray Diffraction (XRD, PANalytical Expert PRO with Xcelerator detector) was used to determine phase composition of the powders, both as-received and heat treated. A Cu-Ka radiation source ($\lambda = 0.15406$ nm) was adopted and $\theta - 2\theta$ scans were carried out from 20 to 140°, with a 0.017° step size and a 25 s dwell time, operating at 40 kV and 40 mA.

2.3 SLM samples characterization

Density of the SLM samples was measured with an analytical balance (0.0001 g precision), by adopting the Archimedes principle. Hardness was evaluated by performing HBW 2.5/62.5 Brinell measurements, hence referred to as HB10 where 10 stands for the force/diameter ratio, as reported in the ASTM E10-18 standard. For all samples, the hardness was measured in the as-built condition, within 12 h from the end of the process. Topography of top surfaces was characterized by means of 3D-Digital Microscopy (Hirox KH-7700). Chemical composition of the SLM samples was determined by glow discharge optical emission spectroscopy (GDOES, GDA-650 Spectrum Analytik GmbH), while phase composition was evaluated by XRD, under the same operating conditions used for the powders and already described in Section 2.2.

For metallographic analyses, cross-sections were extracted from SLM samples considering both longitudinal and transverse direction, with respect to the building one. Subsequently, the cross-sections were prepared for the microstructural characterization following standard metallographic procedures and chemically etched with Keller's reagent (20 s immersion at room temperature) [29]. Metallographic specimens were observed by means of an optical microscope (OM, Zeiss Imager A1) and by SEM-EDS, then porosity measurements and defects characterization were performed using the ImageJ software.

3. Results and discussion

3.1 Powders quality

Representative SEM micrographs of L and H free powders and powders cross-section, in the as-received condition, are reported in Figure 1. Particles of powder H were generally more spherical than powder L, where elongated particles were more present. In the case of powder H, several small and almost perfectly spherical particles can be found; the same doesn't apply to powder L. As shown in Figure 1(a,b), the surface morphology of both set of powders was irregular, since numerous satellites and collapsed particles can be recognized on the surfaces. The analysis of powders cross-section, reported in Figure 1(c,d), showed that they were characterized by a dendritic phase (as highlighted by the optical micrograph in the inset) and they were mainly defect-free, even if in few cases typical solidification defects such as gas porosities, interdendritic shrinkages and possibly bi-film oxides were detected [30]. As for the latter, semi-quantitative chemical analyses obtained by means of SEM-EDS are reported in Figure 2, revealing a higher content of Si and O in correspondence of such defects (Spectra 1 and 2), with respect to the A357 alloy (Spectrum 3).



Figure 1: Representative SEM images of as-received powders: a) and c) free powders and powders cross-sections for powder L, b) and d) free powder and powders cross-sections for Powder H. In the inset, an optical micrograph showing dendritic phase of powders.



 Element (wt.%)

 AI
 Si
 Mg
 O

 Spectrum 1
 88.53
 9.90
 0.34
 1.23

 Spectrum 2
 84.98
 11.2
 0.28
 3.52

 Spectrum 3
 95.65
 3.42
 0.28
 0.62

Figure 2: Results of SEM-EDS analysis performed on powders cross-section.

Size and shape of powder particles were measured via image analysis on SEM micrographs of free particles both in the as-received and pre-treated conditions (200°C for 1h and 60°C for 3h). Results, in terms of major axis and aspect ratio of the particles, are reported in Figure 3. These two parameters were chosen to characterize the powders since major axis quantifies the maximum dimension while the aspect ratio determines the roundness of the particles, being the ratio between the major and the minor axis. The size distribution of both powder L and H, ranging from 5 to 80 μ m, is asymmetric and a positive skewness can be recognized, meaning that the size of the majority of particles lies at low values. In particular, in the as-received condition almost 40% of powders L and H had an axis major below 25 μ m. Moreover, if only small powders with a size up to 10 μ m are considered, the percentage is 8.5 for powder L and 30.8 for powder H, showing that the latter had a consistent amount of small particles. This data confirms that an irregular shape of powder grains increases cohesive forces between particles [31].



Figure 3: Results of particles analysis: a) and c) axis major and aspect ratio for powder L, b) and d) axis major and aspect ratio for Powder H.

The percentage of particles with dimensions greater than 45 μ m was, however, similar for both powders, being 13.1 for powder L and 12.4 for powder H. By comparing the results obtained by image analysis and the ones given by the supplier and retrieved by laser diffraction (Table 2), it appears that the analysis performed via laser diffraction slightly overestimated the size of powder particles.

Furthermore, Figure 3 shows that, after the pre-treatment, the percentage of small particles (with major axis less than 15 μ m) is lower than in the as-received condition, in particular for powder H. The result is confirmed also by SEM images reported in Figure 4. The apparent loss of small particles can be explained in the reason of the cohesion forces action [18,19,32]. For small particles, indeed, the cohesive forces are able to agglomerate powders and this phenomenon is accentuated if the temperature rises. When the particles size increases, the ratio between the weight of a single particle and the cohesive force acting on it increases, making the forces unable to stabilize the cohesion between powder grains.



Figure 4: Representative SEM images of powders in: a) as-received condition, b) after a 60°C preheating and c) after a 200 °C pre-heating.

In addition, image analysis demonstrated that particles belonging to powder H are significantly more spherical than powder L: 31.8% of particles of powder H exhibited an aspect ratio from 1 to 1.1, thus almost perfectly spherical, with respect to 5.4% for powder L. By focusing on particles with the aspect ratio up to 1.5, the percentage raise up to 77.3 for powder H and only 47.4 in case of powder L. In addition, it is worth mentioning that a non-negligible number of powder L particles, 4.7% of the total, had an aspect ratio greater than 3, meaning that almost 5% of powder L was made of strongly elongated particles. Pre-heating treatments seems not to have affected the shape of powders, since only small differences occurred in the measurements, ascribable to experimental variance.

In Figure 5 XRD spectra of both powder L and H, in the as-received and heat-treated conditions, are compared. Al is the main phase detected (ICDD:4-0787), but also minor peaks of silicon (ICDD:27-1402) and alumina can be recognized. In particular, the peak located at 25.4° is consistent with α -Al₂O₃ phase (ICDD:46-1212) [33]. By focusing on the range between 20 and 30° (Figure 5b), it is possible to appreciate that the α -Al₂O₃ was detected neither in powder L nor H after the treatment at 60°C for 3h, while it was found in the as-received powder and also after the treatment at 200°C for 1h. Superficial oxidation is a known issue that concerns AM powders. In a recent study carried out on different materials [34], XPS analyses showed the presence of a thin layer of oxide on the surface of powders in the as-received condition, even if produced with advanced technologies such as VIGA and plasma atomization.



Figure 5: XRD patterns for both powder L and H in the as-received and pre-treated conditions: a) general view of the whole spectra, b) detail of the range $20^{\circ} < 2\theta < 30^{\circ}$

Given the tendency of aluminum to react with oxygen and to form aluminum oxide, as well as the high surface-to-volume ratio in the case of micron-sized powders, it is reasonable that aluminum oxide was detected by XRD analyses. After the heat treatment at 60°C for 3 h the peak of α -Al₂O₃ phase disappeared: it can be argued that the brittle alumina surface layer experienced thermal shock and developed cracks during the heat treatment, due to tensile stresses induced by the thermal expansion of aluminum powders. The α -Al₂O₃ phase was observed again after the heat treatment at 200°C: it is possible that aluminum oxide still experienced thermal shock but the high temperature promoted the formation of a new oxide

layer. In fact, by comparing the integrated diffraction intensity of the AI [111] peak located at 38.5° and the one of α -Al₂O₃ [012] peak located at 25.4° (Table 4), it can be argued that after the heat treatment aluminum oxide phase raised for both powders, and the increase was more consistent in case of powder H.

Table 4: Ratio between the areas of AI [111] and AI_2O_3 [012] peaks resulting from XRD analyses, for powder L and H in the as-received condition and after 200°C for 1h treatment.

Powder	Condition	Al ₂ O ₃ /Al
L	As-received	0.031
Н	As-received	0.038
L	200°C x 1h	0.037
Н	200°C x 1h	0.058

3.2 Effect of SLM parameters

In Figure 6 the density of SLM samples, as a function of laser power, is reported. In order to compare all results, in the same plot both data of samples produced with powder pre-heated at 60°C and 200°C are displayed. Density of samples strictly depends on laser power: for powder H the relation between power and density was almost linear and, by increasing the power, the density of SLM samples increased accordingly. Powder L, instead, presented a threshold value of 110 W, since only in case of laser power beyond 110 W, the density increased linearly with the power. It is well known that one of the major complications of processing aluminum with SLM is the formation of thin oxide layer on the free surface of the melt pool, even if the process is carried out in an inert atmosphere with very low level of oxygen [35]. Thus, in order to successfully consolidate subsequent layers, it is necessary to break the oxide film by operating with high laser power. Furthermore, it has to be taken into consideration that, due to the low absorptivity of aluminum, most of the irradiance of the laser beam is reflected [4], but the efficiency of the process can be improved by exploiting the multiple scattering phenomena occurring among powder particles [36]. Multiple scattering is promoted by spherical powders and, indeed, samples obtained with powder H, being more spherical than powder L, always exhibited higher density, even for values of laser power lower than 110W, at which powder L exhibited the poorest density. As a consequence, it can be assumed that elongated particles, which are more numerous in powder L, negatively affected the multiple scattering between particles. In addition, the greater flowability of powder H with respect to powder L (Table 2), that is strongly related with the sphericity of particles [22], has likely promoted the spreading of an even and compacted layer during the process. Finally, even though it is not possible to quantify the packing of powders from particles analysis and axis major distribution (Fig.3), a wide size distribution of spherical powders (as in case of powder H) generally promotes packaging and increase density of final samples. This consideration agrees with the results obtained in relation to the higher density of the samples realized from powder H, compared to those printed with L.

The influence of scanning velocity is evident in case of powder H (Fig. 6c,d) where, for a given laser power, the lowest scanning velocity resulted in samples with maximum density. As already reported in the literature [37,38], spattering and denudation phenomena can be responsible for the formation of porosities and they are strongly related to laser power and scanning velocity. At high scanning velocities the two phenomena are accentuated, therefore is probable that, for a given laser power, samples processed with the highest scanning velocity had a major content of porosities. Samples obtained from powder L, instead, were more influenced by powder pre-treatment than scanning velocity. As reported in Fig. 6a,b, the low temperature pre-treatment maximized density and minimized the contribution ascribable to the scanning velocity; this results is quite evident by focusing on the samples processed at 170 W. More generally, in terms of density all H and L samples benefited from the powder heat-treatment carried out at 60°C. As mentioned before, powders treated at 200°C exhibited Al₂O₃, possibly an oxide layer on the powders surface. Thus, in order to melt the powder particles higher power is necessary, with respect to the powder dried at 60°C, where the oxide layer is not present.



Figure 6: Results of density measurements as a function of laser power and scanning velocities: a) samples produced with powder L, c) samples produced with powder H, b) and d) details on samples produced ad higher power for powders L and H respectively. Numerical data are supplied as supplementary material (Table S1).

The HB10 hardeness of samples as a function of laser power, for both powders and pretreatments, is reported in Figure 7. By increasing the power the hardness increases, for both powder H and L, as showed by Figure 7(a,c). The lowest hardness measured was approx. 50-60 HB10 in case of low density samples while, for samples with the highest density, a maximun of approx. 103 and 108 HB10 were assessed for powder L and H, respectively (Figure 7(b,d)). The conventional A357 cast alloy reaches the value up to 100 HB only after the T6 heat treatment [39], in the present study, instead, the hardness was measured in the as-built samples, within 12 h from the end of the process. Therefore the SLM process itself succeeded, in the reason of the fine resulting microstructure [6], in obtaining an hardness comparable and even higher than the conventional heat-treated alloy. The low temperature pre-treatment resulted in samples with greater hardness than the corresponding ones obtained with powders exposed at the high temperature. This results is highlighted by the details in Figure 7(b,d) for the samples with superior density.



Figure 7: Results of hardness measurements as a function of laser power and scanning velocities: a) samples produced with powder L, c) samples produced with powder H, b) and d) details on samples produced ad higher power for powders L and H respectively. Numerical data are supplied as supplementary material (Table S1).

The chemical composition of SLM samples was evaluated with GD-OES, in case of samples processed with the highest energy density (Table 5). It is well known [5] that high energy densities might lead to metal vaporization, thus, the control of the chemical composition is necessary. By comparing the results on Table 5 with the requirements for the A357 alloy given by EN 1706 standard, it can be argued that chemical composition of samples obtained with powder H complies with the standard. On the other hand, the Mg content of powder L samples is slightly lower than the one required for the A357 alloy.

Table 5: Chemical composition, measured by GD-OES, of samples produced with the highest volume energy density (P=170W, v=500 mm/s, E=242.9 J mm⁻³) considering both powders and pre-treatment conditions

Doudor	Dro Troofmont	Element (wt.%)						
Powder	Pre-meatment -	AI	Si	Mg	Ti	Fe	Zn	
L	60°C x 3h	92.445	6.842	0.429	0.103	0.071	0.072	
L	200°C x 1h	92.236	6.902	0.410	0.108	0.099	0.083	
Н	60°C x 3h	92.397	6.687	0.565	0.150	0.085	0.069	
Н	200°C x 1h	92.356	6.795	0.571	0.123	0.049	0.066	

The phase composition of selected SLM samples is reported in Figure 8, where representative samples processed with a constant scanning speed of 900 mm/s and a power of 70 and 150 W are compared, for powder L and H pre-treated at 200°C.



Figure 8: XRD patterns for samples produced with powder L and H (pre-treated at 200°C for 1 h) with a scanning velocity of 900 mm/s, in the as-built conditions.

The only phases detected are Al and Si, so, the Al₂O₃ phases that was observed in the pretreated powder was not present in the samples. By operating at the highest laser power (170W) it was possible to obtain a density close to 98% in case of powder L and over 99% in case of powder H (being 2.68 g/cm³ the reference value for a A357 cast alloy [39]). Nevertheless, by observing the cross-sections of samples processed at 170W few defects could be recognized. Thus, the measurement of the total area occupied by porosities was performed via image analysis, and results are reported in Table 6. The percentage of porosity detected on the cross-section is higher in the case of samples produce with powder L, confirming the results of the density measurement. In addition, results showed that samples with the lowest content of porosity are the ones processed with the highest energy density (170W, 500 mm/s) and adopting the 60°C heat-treatment for powders. However, densities obtained via image analysis are lower than those measured following the Archimedes principle, so, a deeper investigation was carried out by comparing morphological and microstructural features, as reported in Figure 9.

Sample	Powder Pre-treatment	Powder	Porosity on cross section [%]	Presence of spatters in the inspected areas [%]	Mean spatters diameter [µm]
170W-	60° x 3h	L	1.75	73.3	399 ± 112
500mm/s		Н	0.90	20.0	427 ± 75
170W-	200°C x 1b	L	4.97	66.7	424 ± 112
500mm/s	200 0 X III	Н	1.07	40.0	382 ± 98
170W-	60° x 3h	L	2.05	80.0	247 ± 105
1200mm/s		Н	2.30	40.0	382 ± 98
170W-	200°C x 1b	L	3.72	86.7	249 ± 121
1200mm/s	200 0 X III	Н	2.61	46.7	290 ± 50

Table 6: Results of image analysis performed on cross-sections of SLM samples

On the cross-section of samples, large material discontinuities, with dimensions greater than 200 μ m, were found, as shown in Figure 9(a,c). These discontinuities consisted of a round area with a coarser microstructure with respect of the regular microstructure that surrounded the defect, with a cavity lying beneath. It is possible that these large cavities were filled with unmelted powder particles, that have been released during the metallographic preparation, thus explaining why density measured by Archimedes principle was overestimated. The round area with a coarse microstructure can be related to the spattering phenomena. As already reported by other researchers [40], who investigated morphological aspects of A357 processed by SLM, spattering, balling and un-melted powder particles can be found on the surfaces, and un-melted particles and spatters can be distinguished by their microstructure since cooling rates of powders are higher than spatters. In the present study, the majority of powders particles have been proved to be smaller than 60 μ m, so it is unlikely that these defects might be related to un-melted particles. In their work [40], indeed, they showed spatters with dimension greater than 200 μ m with consistent gas porosity content. With the aim to correlate the defects

observed on cross-sections with spatters generation, morphological and microstructural features were compared.



Figure 9: Results of spatters analysis: a) and c) optical micrograph of sample cross-section showing a spatters defect for powder L and H respectively; b) and d) 3D maps of top surfaces of a representative sample for powder L and H respectively.

As regards morphological features, 3D maps of samples top surfaces were acquired with the 3D digital microscope, as showed in Figure 9 (b,d) for samples processed with laser power 170W and scanning velocity 1200 mm/s. Top surfaces were chosen for the analysis since they represent the last processed layer. 3D maps revealed the presence on the surfaces of large spatters with a maximum height of about 270 µm. On the cross-sections, a fixed number of zones were investigated on each sample and for every zone it was recorded the presence, or the absence, of the defect. So, the percentage of spatters identified on the cross-section was evaluated. Furthermore, when a defect was detected, it was measured via image analysis. The results of spatters analysis, also reported in Table 6, demonstrated that a larger extent of such defects was found on samples obtained with powder L than powder H, by a factor of about two. In addition, by comparing the dimensions measured by image analysis with the morphological investigation in Figure 9 (b,d), spatters were positively related to the microstructural defects

detected on-cross sections. Spatters are generated during the SLM process and they consist of molten material ejected by the melt pool, then, once solidified, landed on the layer being processed [41, 37]. It can be argued that, since dimension of spatters are considerably greater than layer thickness and powder particles, they can negatively affect the deposition and the melting of the subsequent layer, as illustrated by Wang et al. [40], therefore they can generate microstructural defects. It is worth noting that, both in the case of powder L and H, by increasing the scanning velocity the amount of spatters defects on cross-section increased accordingly, but their dimension decreased.

Spatter defects were finally analyzed with the aid of SEM-EDS: as disclosed in Figure 10, spatters defects had high content of spherical gas porosities with dimension lower than 10 μ m. In the large cavity underlying the spatter, melted and semi-melted material can be found and the EDS analysis evidenced the presence of elevated concentrations of oxygen in the cavity (Spectra 2,3,4) with respect to the reference material (Spectrum 1).



		Eleme	ent (wt.%)	
	AI	Si	Mg	0
Spectrum 1	90.98	7.38	0.34	1.30
Spectrum 2	60.49	3.21	1.94	34.36
Spectrum 3	78.84	5.37	0.00	15.79
Spectrum 3	82.27	7.10	0.37	10.26

Figure 10: Results of SEM-EDS analysis performed on a spatter defect detected on sample crosssection

4. Conclusions

Density, hardness and microstructural defects of A357 samples produced by SLM have been analysed with regard to the feedstock material. Experiments have been carried out with the aim of investigating the effect of the powder conditions in terms of size, morphology and pre-treatment on the properties of the final components. Based on the outcomes of the present

work, the following conclusions can be drawn by separately discussing the influence of the different factors involved in the study.

From powder morphology point of view:

- For the same process parameters, the powder with particles more spherical than elongated (as powder H) allowed to obtain samples with the highest densities, probably by the reason of the enhanced flowability of the powder.
- Spherical powders reduced the spattering phenomenon and, consequently, the presence of microstructural defects decreased.

The comparison between results obtained with or without pre-treatment of the powder is even more relevant:

- As-received powders had a greater number of particles with a diameter ≤ 15 μm compared to the pre-treated ones. Heat treatment of powders probably promoted the aggregation of smaller particles.
- Pre-treatment did not directly affect the morphology of the powders but, in case of the powder with the highest amount of very small particles (≤ 10 µm), the percentage of particles with aspect ratio 1 / 1.1 decreased with pre-treatment. As mentioned above, this result is probably due to the aggregation phenomena that facilitated the smaller powders to become satellites of the larger ones.
- XRD analyses evidenced the Al₂O₃ phase both in the as-received powder and pretreated at 200°C. On the contrary, powders pre-treated at 60 °C did not exhibit the presence of aluminium oxide.
- Powder pre-treated at 60°C resulted in samples with higher density and hardness if compared to the analogue ones obtained from powder pre-treated at 200°C.
- For the powder with the highest amount of spherical particles, the presence of spatter defects on samples cross-section was twice in the case of pre-treatment at 200 °C compared to the 60 °C one.

Finally, with regards to the process parameters, it is possible to state that:

- High energy density was necessary to reduce porosity.
- In case of high energy density, it was also possible to obtain the greatest hardness values. Among the samples with greater hardness, however, the highest values were obtained for the maximum laser scanning speed, probably as a consequence of the different cooling rate.

- High scanning speeds promoted the formation of spattering, identified by the presence of large microstructural discontinuities; however, the average dimension of such discontinuities was greater in the case of low scanning speed.

5. Acknowledgment

The authors would like to thanks Dr Iuri Boromei at the University of Bologna for his precious contribution in SEM-EDS and XRD analyses.

This research did not receive any specific grant from funding agencies in the public, commercial, or not-for-profit sectors.

Declarations of interest: none.

References

[1] Mishurova, T., Artzt, K., Haubrich, J., Requena, G., Brunoa, G., New aspects about the search for the most relevant parameters optimizing SLM materials, Additive Manufacturing 25, (2019) 325-334, doi.org/10.1016/j.addma.2018.11.023.

[2] Khorasani, A.M., Gibson, I., Awan, U.S., Ghaderi, A., The effect of SLM process parameters on density, hardness, tensile strength and surface quality of Ti-6AI-4V, Additive Manufacturing 25, (2019) 176-186, doi.org/10.1016/j.addma.2018.09.002.

[3] Liverani, E., Toschi, S., Ceschini, L., Fortunato, A., Effect of Selective Laser Melting (SLM) process parameters on microstructure and mechanical properties of 316L austenitic stainless steel, Journal of Materials Processing Technology 249, (2017) 255-263, doi.org/10.1016/j.jmatprotec.2017.05.042.

[4] Galy, C., Le Guen, E., Lacoste, E., Arvieu, C., Main defects observed in aluminum alloy parts produced by SLM: From causes to consequences, Additive Manufacturing 22, (2018) 166-175, doi.org/10.1016/j.addma.2018.05.005.

[5] Collins, P.C., Brice, D.A., Samimi, P., Ghamarian, I., Fraser, H.L., Microstructural Control of Additively Manufactured Metallic Materials, Annual Review of Materials Research 46, (2016) 63-91, doi.org/10.1146/annurev-matsci-070115-031816.

[6] Sames, W. J., List, F. A., Pannala, S., Dehoff R. R., Babu, S. S., The metallurgy and processing science of metal additive manufacturing, International Materials Reviews 61:5, (2016) 315-360, doi.org/10.1080/09506608.2015.1116649.

[7] Bartlett, J.L., Li, X., An overview of residual stresses in metal powder bed fusion, Additive Manufacturing 27 (2019) 131-149, doi.org/10.1016/j.addma.2019.02.020.

[8] Parry, L.A., Ashcroft, I.A., Wildman, R.D., Geometrical effects on residual stress in selective laser melting, Additive Manufacturing 25 (2019) 166-175, doi.org/10.1016/j.addma.2018.09.026.

[9] Yamaguchi, H., Fergani, O., Wua, P., Modification using magnetic field-assisted finishing of the surface roughness and residual stress of additively manufactured components, CIRP Annals - Manufacturing Technology 66, (2017) 305-308, doi.org/10.1016/j.cirp.2017.04.084.

[10] Kaynaka, Y., Kitay, O., The effect of post-processing operations on surface characteristics of 316L stainless steel produced by selective laser melting, doi.org/10.1016/j.addma.2018.12.021.

[11] Fortunato, A., Lulaj, A., Melkote, S., Liverani, E., Ascari, A., Umbrello, D., Milling of maraging steel components produced by selective laser melting, International Journal of Advanced Manufacturing Technology 94, (2018) 1895-1902, 10.1007/s00170-017-0922-9.

[12] Anderson, I.E., White, E.M.H, Dehoff, R., Feedstock powder processing research needs for additive manufacturing development, Current Opinion in Solid State and Materials Science 22, (2018) 8-15, doi.org/10.1016/j.cossms.2018.01.002.

[13] Tan, J.H., Wong, W.L.E., Dalgarno, K.W., An overview of powder granulometry on feedstock and part performance in the selective laser melting process, Additive Manufacturing 18, (2017) 228-255, doi.org/10.1016/j.addma.2017.10.011.

[14] Pleassa, C., Jothia, S., Influence of powder characteristics and additive manufacturing process parameters on the microstructure and mechanical behaviour of Inconel 625 fabricated by Selective Laser Melting, Additive Manufacturing 24, (2018) 419-431, doi.org/10.1016/j.addma.2018.09.023.

[15] Nguyen, Q.B., Nai, M.L.S., Zhu, Z., Sun, C.-N., Wei, J., Zhou, W., Characteristics of Inconel powders for powder-bed additive manufacturing, Engineering 3, (2017) 695–700, doi.org/10.1016/J.ENG.2017.05.012.

[16] Spierings, A.,B., Levy, G., Comparison of density of stainless steel 316L parts produced with selective laser melting using different powder grades, Annual International SFF Symposium, Austin, University of Texas, (2009) 342–353.

[17] Spierings, A.,B., Herres, N., Levy, G., Influence of the particle size distribution on surface quality and mechanical properties in AM steel parts, Rapid Prototyping Journal 17(3), (2011) 195-202, 10.1108/13552541111124770.

[18] Karapatis, N.P., A sub-process approach of selective laser sintering. 2002, Ecole Polytechnique fédérale de Lausanne EPFL: Lausanne, 10.5075/epfl-thesis-2506.

[19] Baitimerov, R., Lykov, P., Zherebtsov, D., Radionova, L., Shultc, A., & Prashanth, K. G., Influence of Powder Characteristics on Processability of AlSi12 Alloy Fabricated by Selective Laser Melting, Materials 11(5), (2018) 742, 10.3390/ma11050742.

[20] Muñiz-Lerma, J.A., Nommeots-Nomm, A., Waters, K.E., Brochu, M., A Comprehensive Approach to Powder Feedstock Characterization for Powder Bed Fusion Additive Manufacturing: A Case Study on AlSi7Mg, Materials 11, (2018) 2386, 10.3390/ma11122386.

[21] Hebert, R.J., Viewpoint: metallurgical aspects of powder bed metal additive manufacturing Journal of Materials Science 51, (2016) 1165-1175, 10.1007/s10853-015-9479-x.

[22] Vock, S., Klöden, B., Kirchner, A., Weißgärber, T., Kieback, B., Powders for powder bed fusion: a review. Progress in Additive Manufacturing, (2019) 1-15, doi.org/10.1007/s40964-019-00078-6.

[23] Asgaria, H., Baxtera, C., Hosseinkhani, K., Mohammadi, M., On microstructure and mechanical properties of additively manufactured AlSi10Mg_200C using recycled powder, Materials Science & Engineering A 707, (2017) 148-158, doi.org/10.1016/j.msea.2017.09.041.

[24] Clayton, J., Millington-Smith, D., Armstrong, B., The application of powder rheology in additive manufacturing, Journal of the Minerals, Metals & Materials Society 67, (2015) 544–548, 10.1007/s11837-015-1293-z.

[25] Li, X.P., O'Donnell, K.M., Sercombe, T.B., Selective laser melting of Al-12Si alloy: Enhanced densification via powder drying, Additive Manufacturing 10, (2016) 10-14, doi.org/10.1016/j.addma.2016.01.003.

[26] Cayless, R.B.C., Alloy and Temper Designation Systems for Aluminum and Aluminum Alloys, Properties and Selection: Nonferrous Alloys and Special-Purpose Materials, ASM Handbook, 1990. doi.org/10.31399/asm.hb.v02.9781627081627

[27] Carpenter Technology Corporation, Available: www.carpenteradditive.com

[28] Rueden, C. T., Schindelin, J., Hiner, M. C., DeZonia, B.E., Walte, A.E., Arena, E.T., Eliceiri, K.W., ImageJ2: ImageJ for the next generation of scientific image data, BMC Bioinformatics 18(1), (2017) 529, doi:10.1186/s12859-017-1934-z

[29] Vander Voort, G.F., ASM Handbook Volume 9 - Metallography and Microstructures, ASM International, 2004.

[30] Fiorese E., Bonollo, F., Timelli, G., Arnberg, L., Gariboldi, E., New Classification of Defects and Imperfections for Aluminum Alloy Castings, InternationI Journal of Metalcasting 9(1), (2015) 55-66, doi:10.1007/BF03355602.

[31] O.R. Walton. Review of Adhesion Fundamentals for Micron Scale Particles, Kona Powder and Particle Journal 26(26), 129-141, doi.org/10.14356/kona.2008012.

[32] Yablokova, G., Speirs, M., Van Humbeeck, J., Kruth, J.-P, Schrooten, J., Cloots, R., Boschini, F., Lumay, G., Luyten, J., Rheological behavior of β -Ti and NiTi powders produced by atomization for SLM production of open porous orthopedic implants, Powder Technology 283, (2015) 199-209, doi.org/10.1016/j.powtec.2015.05.015.

[33] Lamouri, S., Hamidouche, M., Bouaouadja, N., Belhouchet, H., Garnier, V., Fantozzi, G., Trelkat, J.F., Control of the γ -alumina to α -alumina phase transformation for an optimized alumina densification.

Boletín de la Societad Española de Cerámica y Vidrio 6(56), (2016) 47-54, doi:10.1016/j.bsecv.2016.10.001.

[34] Hryha, E., Shvab, R., Gruber, H., Leicht, A., Nyborg, L., Surface Oxide State on Metal Powder and its Changes during Additive Manufacturing: an Overview, La Metallurgia Italiana 3, (2018) 34-39.

[35] Louvis, E., Fox, P., Sutcliffe, C.J., Selective laser melting of aluminium components. Journal of Materials Processing Technology 211(2), (2011) 275-284, doi:10.1016/j.jmatprotec.2010.09.019.

[36] Boley, C.D., Khairallah, S.A., Rubenchik, A.M., Calculation of laser absorption by metal powders in additive manufacturing. Applied Optics 54(9), (2015) 2477-2482, doi.org/10.1364/AO.54.002477.

[37] Bidare, P., Bitharas, I., Ward, R.M., Attallah, M.M., Moore, A.J., Fluid and particle dynamics in laser powder bed fusion, Acta Materialia 142, (2018) 107–120, doi:10.1016/j.actamat.2017.09.051.

[38] Matthews, M.J., Guss, G., Khairallah, S.A., Rubenchik, A.M., Depond, P.J., King, W.E., Denudation of metal powder layers in laser powder bed fusion processes, Acta Materialia 114, (2016) 33–42, doi:10.1016/j.actamat.2016.05.017.

[39] Sigworth, G., Aluminum Casting Alloys and Casting Processes, Aluminum Science and Technology, ASM Handbook, (2018), doi.org/10.31399/asm.hb.v02a.9781627082075

[40] Nasab, M.H., Gastaldi, D., Lecis, N.F., Vedani M., On Morphological Surface Features of the Parts Printed by Selective Laser Melting (SLM). Additive Manufacturing 24, (2018) 373-377, doi:10.1016/j.addma.2018.10.011.

[41] Wang, D., Wu, S., Fu, F., Mai, S., Yang, Y., Liu, Y., Song, C., Mechanisms and characteristics of spatter generation in SLM processing and its effect on the properties, Materials & Design 117, (2017) 121–130, doi:10.1016/j.matdes.2016.12.060.